


WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

Machine Id

EASG1012783

Diesel Engine							
{not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number	OOW	Client Info	LITTIOTALIT	WC0910938		
	Sample Date		Client Info		06 May 2024		
	Machine Age	hrs	Client Info		0	1515	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		Changed	Changed	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	>100	8	13	
WEAR	Chromium	ppm	ASTM D5185m		<1	<1	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0	0	
	Titanium	ppm	ASTM D5185m	77	0	11	
	Silver	ppm	ASTM D5185m	>3	<1	0	
	Aluminum	ppm	ASTM D5185m		2	4	
	Lead	ppm	ASTM D5185m		- <1	<1	
	Copper	ppm	ASTM D5185m		2	5	
	Tin	ppm	ASTM D5185m		- <1	0	
	Vanadium	ppm	ASTM D5185m		<1	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon		ACTM DE10Em	. 05	4	E	
CONTAMINATION		ppm	ASTM D5185m		0	5 8	
There is no indication of any contamination in the oil.	Potassium Fuel	ppm	ASTM D5185m WC Method		-	<1.0	
	Water		WC Method		<1.0 NEG	NEG	
	Glycol		WC Method	>0.2	NEG	NEG	
	Soot %	%	*ASTM D7844	~3	0.2	0.1	
	Nitration	Abs/cm	*ASTM D7624	>20	7.9	9.3	
	Sulfation	Abs/.1mm	*ASTM D7415		20.8	18.3	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
ELUID CONDITION	Codium		ACTM DE10Em		40	Е	
FLUID CONDITION	Sodium Boron	ppm	ASTM D5185m		12	5	
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m ASTM D5185m		282 0	109 0	
	Molybdenum	ppm	ASTM D5185m		82	36	
	Manganese	ppm	ASTM D5185m		o2 <1	2	
	Magnesium		ASTM D5185m		457	658	
	Calcium	ppm	ASTM D5185m		1817	1454	
	Phosphorus	ppm	ASTM D5185m		1068	574	
	Zinc	ppm	ASTM D5185m		1270	767	
	Sulfur	ppm	ASTM D5185m		3704	2277	
	Oxidation	Abs/.1mm	*ASTM D7414	>25	16.4	14	
	Base Number (BN)			7 2 3	7.8	7.9	
	Visc @ 100°C	cSt	ASTM D445		12.6	13.5	







Certificate L2367

Laboratory Sample No.

: WC0910938 Lab Number : 06188447 Unique Number : 11045199 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

: 22 May 2024 **Tested** : 24 May 2024 Diagnosed : 24 May 2024 - Wes Davis

DOLE FRESH FRUIT PO BOX 725, ATTN: MAINTENANCE AND REPAIR

NEW CASTLE, DE US 19720

Contact: LUIS LAPIERRE luis.lapierre@dole.com T: (302)652-6344

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: LUIS LAPIERRE - DOLWIL