



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
VOLVO 21826
Component
Diesel Engine
Fluid
SHELL ROTELLA T 10W30 (38 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0909734	WC0866905	WC0729277
Sample Date		Client Info		17 May 2024	19 Oct 2023	25 Nov 2022
Machine Age	mls	Client Info		264647	242720	221030
Oil Age	mls	Client Info		21927	12058	24333
Filter Age	mls	Client Info		21927	12058	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	56	31	52
Chromium	ppm	ASTM D5185m	>20	2	1	1
Nickel	ppm	ASTM D5185m	>2	4	4	<1
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>2	1	1	0
Aluminum	ppm	ASTM D5185m	>25	5	11	3
Lead	ppm	ASTM D5185m	>40	5	9	7
Copper	ppm	ASTM D5185m	>330	8	31	4
Tin	ppm	ASTM D5185m	>15	2	2	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	8	11	6
Potassium	ppm	ASTM D5185m	>20	11	6	6
Fuel		WC Method	>6.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.4	0.8
Nitration	Abs/cm	*ASTM D7624	>20	10.9	9.4	10.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	27.3	21.2	29.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	3	4
Boron	ppm	ASTM D5185m	269	31	30	30
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m	0	12	41	6
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	20	90	301	41
Calcium	ppm	ASTM D5185m	1521	2130	1836	2068
Phosphorus	ppm	ASTM D5185m	948	886	1060	874
Zinc	ppm	ASTM D5185m	893	1203	1182	1126
Sulfur	ppm	ASTM D5185m		3334	3775	3375
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.4	17.6	22.9
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	4.9	6.5	5.3
Visc @ 100°C	cSt	ASTM D445	11.0	11.8	11.9	11.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0909734
Lab Number : 06188696
Unique Number : 11045448
Test Package : FLEET

Received : 23 May 2024
Tested : 24 May 2024
Diagnosed : 28 May 2024 - Sean Felton

GUY M TURNER & TURNER TRANSFER
 4505 SOUTH HOLDEN ROAD
 GREENSBORO, NC
 US 27406

Contact: ROGER HIXSON
 rhixson@guyturner.com

T: (336)294-4660
 F: (336)294-6644

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)