



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
264/E-6
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0868261	WC0699207	WC0699183
Sample Date		Client Info		16 May 2024	07 Dec 2023	26 Jun 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	8	7	5
Chromium	ppm	ASTM D5185m	>20	<1	<1	2
Nickel	ppm	ASTM D5185m	>4	<1	<1	1
Titanium	ppm	ASTM D5185m		0	<1	2
Silver	ppm	ASTM D5185m	>3	<1	0	2
Aluminum	ppm	ASTM D5185m	>20	7	6	5
Lead	ppm	ASTM D5185m	>40	<1	<1	4
Copper	ppm	ASTM D5185m	>330	30	35	21
Tin	ppm	ASTM D5185m	>15	3	3	3
Vanadium	ppm	ASTM D5185m		<1	0	1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	6	6	6
Potassium	ppm	ASTM D5185m	>20	2	4	7
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.3	0.2
Nitration	Abs/cm	*ASTM D7624	>20	8.7	8.3	6.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.2	24.2	24.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	1	0	3
Boron	ppm	ASTM D5185m	250	274	287	321
Barium	ppm	ASTM D5185m	10	0	11	0
Molybdenum	ppm	ASTM D5185m	100	137	131	114
Manganese	ppm	ASTM D5185m		<1	<1	2
Magnesium	ppm	ASTM D5185m	450	720	654	685
Calcium	ppm	ASTM D5185m	3000	1795	1546	1595
Phosphorus	ppm	ASTM D5185m	1150	752	657	679
Zinc	ppm	ASTM D5185m	1350	924	849	843
Sulfur	ppm	ASTM D5185m	4250	2847	2698	2922
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.6	18.0	16.6
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	7.5	7.9	9.2
Visc @ 100°C	cSt	ASTM D445	14.4	13.8	14.1	13.8


FT-IR (Direct Trend)




Ferrous Alloys




Base Number




Non-ferrous Metals




Viscosity @ 100°C



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0868261 **Received** : 23 May 2024
Lab Number : 06188820 **Tested** : 24 May 2024
Unique Number : 11045572 **Diagnosed** : 24 May 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

CYFAIR FIRE DEPARTMENT
 10710 TELGE RD
 HOUSTON, TX
 US 77095
 Contact: JEFF DAVIDSON
 jeff.davidson@cyfairfd.org
 T: (281)656-3440
 F: (281)807-1853

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)