IND II WEAR CHECK

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	ABNORMAL
FLUID CONDITION	NORMAL

Machine Id
QUINCY 3 EAST (S/N UTY201699)
Component
Air Compressor
Fluid
USPI AIR 46 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

WEAR

All component wear rates are normal.

CONTAMINATION

There is a light concentration of water present in the oil. The amount and size of particulates present in the system are acceptable.

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		**USPM36243**	USPM30068	USPM31252
Sample Date		Client Info		**18 May 2024**	12 Feb 2024	04 Nov 2023
Machine Age	hrs	Client Info		**50858**	50671	49413
Oil Age	hrs	Client Info		**0**	0	0
Filter Age	hrs	Client Info		**0**	0	0
Oil Changed		Client Info		**N/A**	N/A	N/A
Filter Changed		Client Info		**N/A**	N/A	N/A
Sample Status				**ABNORMAL**	NORMAL	NORMAL
Iron	ppm	ASTM D5185m	>50	**0**	0	0
Chromium	ppm	ASTM D5185m	>4	**0**	0	<1
Nickel	ppm	ASTM D5185m	>4	**0**	<1	0
Titanium	ppm	ASTM D5185m		**0**	0	<1
Silver	ppm	ASTM D5185m		**<1**	0	<1
Aluminum	ppm	ASTM D5185m	>10	**0**	<1	0
Lead	ppm	ASTM D5185m	>20	**<1**	<1	0
Copper	ppm	ASTM D5185m	>40	**2**	2	2
Tin	ppm	ASTM D5185m	>5	**<1**	<1	0
Vanadium	ppm	ASTM D5185m		**0**	0	<1
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silicon	ppm	ASTM D5185m	>25	**4**	3	3
Potassium	ppm	ASTM D5185m	>20	**1**	2	<1
Water	%	ASTM D6304	>0.2	▲ **0.219**	0.080	0.081
ppm Water	ppm	ASTM D6304	>2000	▲ **2198**	810	816.6
Particles >4µm		ASTM D7647	>10000	**902**	624	820
Particles >6µm		ASTM D7647	>2500	**157**	70	143
Particles >14µm		ASTM D7647	>320	**5**	4	10
Particles >21µm		ASTM D7647	>80	**1**	1	3
Particles >38µm		ASTM D7647	>20	**0**	0	0
Particles >71µm		ASTM D7647	>4	**0**	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	**17/14/10**	16/13/9	17/14/10
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	**NEG**	NEG	NEG
Sodium	ppm	ASTM D5185m		**2**	1	0
Boron	ppm	ASTM D5185m	0	**2**	2	<1
Barium	ppm	ASTM D5185m	0	**<1**	0	0
Molybdenum	ppm	ASTM D5185m	0	**0**	0	0
Manganese	ppm	ASTM D5185m		**0**	0	0
Magnesium	ppm	ASTM D5185m	0	**1**	0	<1
Calcium	ppm	ASTM D5185m	0	**0**	0	0
Phosphorus	ppm	ASTM D5185m	1	**15**	2	0
Zinc	ppm	ASTM D5185m	0	**0**	0	0
Sulfur	ppm	ASTM D5185m	0	**39**	<1	0
Acid Number (AN)	mg KOH/g	ASTM D8045	0.05	**1.35**	1.27	1.25
Visc @ 40°C	cSt	ASTM D445	49.7	**66.3**	67.9	66.7

Water (KF)



Particle Count



Acid Number



Viscosity @ 40°C



Particle Trend



Ferrous Alloys



Non-ferrous Metals



Viscosity @ 40°C



Particle Count



Acid Number



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : USPM36243
Lab Number : 06189210
Unique Number : 11045962
Test Package : IND 2

Received : 23 May 2024
Tested : 24 May 2024
Diagnosed : 29 May 2024 - Jonathan Hester

Certificate L2367

TYSON-ROBARDS-USP

ROBARDS, KY
US
Contact: SERVICE MANAGER

T:
F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)