

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL

## Area PALASYN 45 [8017634] Machine Id SULLIVAN PALATEK 07G007 - INLAND TRUCK PARTS Component Compressor

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		UCS06189378	UCS05830295	
	Sample Date		Client Info		17 May 2024	20 Apr 2023	
	Machine Age	hrs	Client Info		37488	34957	
	Oil Age	hrs	Client Info		2327	4199	
	Filter Age	hrs	Client Info		2327	1380	
	Oil Changed		Client Info		Not Changd	Changed	
	Filter Changed		Client Info		Changed	Changed	
	Sample Status				NORMAL	NORMAL	
WEAR	Iron	ppm	ASTM D5185m	>50	0	<1	
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	0	0	
	Nickel	ppm	ASTM D5185m		<1	0	
	Titanium	ppm	ASTM D5185m		0	0	
	Silver	ppm	ASTM D5185m		0	0	
	Aluminum	ppm	ASTM D5185m	>25	0	0	
	Lead	ppm	ASTM D5185m	>25	<1	0	
	Copper	ppm	ASTM D5185m	>50	0	0	
	Tin	ppm	ASTM D5185m	>15	<1	0	
	Vanadium	ppm	ASTM D5185m		0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>25	3	1	
	Potassium	ppm	ASTM D5185m	>20	<1	<1	
	Water		WC Method	>0.1	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	LIGHT	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3	0	
The AN level is acceptable for this fluid. The condition of the oil is	Boron	ppm	ASTM D5185m	0.0	0	0	
suitable for further service.	Barium	ppm	ASTM D5185m	0.0	0	0	
	Molybdenum	ppm	ASTM D5185m	0	0	0	
	Manganese	ppm	ASTM D5185m	0	<1	0	
	Magnesium	ppm	ASTM D5185m	0.0	0	<1	
		ppm	ASTM D5185m	0.0	0	0	
	Calcium	PPIII					
	Calcium Phosphorus	ppm	ASTM D5185m	966	548	565	
			ASTM D5185m ASTM D5185m		548 0	565 0	

Acid Number (AN) mg KOH/g ASTM D8045 0.172


cSt


Visc @ 40°C

ASTM D445 39.9 **40.8** 40.1 ---Contact/Location: REUBEN - UCLIFSIO

0.07

0.08





Contact/Location: REUBEN - UCLIFSIO Page 2 of 2