

#### Machine Id **523** Component **2 Differential** Fluid **GEAR OIL SAE 75W90 (--- GAL)**

## RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

#### WEAR

All component wear rates are normal.

#### CONTAMINATION

There is no indication of any contamination in the oil.


### FLUID CONDITION


The condition of the oil is acceptable for the time in service.


Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DC0034728	DC0029596	
Sample Date		Client Info		15 Apr 2024	28 Sep 2023	
Machine Age	mls	Client Info		401509	397898	
Oil Age	mls	Client Info		0	0	
Filter Age	mls	Client Info		0	0	
Oil Changed		Client Info		Changed	N/A	
Filter Changed		Client Info		Changed	N/A	
Sample Status				NORMAL	NORMAL	
Iron	nnm	ASTM D5185m	>500	28	226	
Chromium	ppm	ASTM D5185m	>10	<1	<1	
Nickel	ppm	ASTM D5185m	>10	<1	<1	
Titanium	ppm ppm	ASTM D5185m	>10	<1	1	
Silver	ppm	ASTM D5185m		<1	0	
Aluminum		ASTM D5185m	>25	2	17	
Lead	ppm	ASTM D5185m	>25	2 <1	0	
Copper	ppm	ASTM D5185m	>100	1	1	
Tin	ppm	ASTM D5185m	>10	1	0	
Vanadium	ppm	ASTM D5185m	>10	י <1	<1	
White Metal	ppm scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Scalal	visuai				
Silicon	ppm	ASTM D5185m	>75	6	40	
Potassium	ppm	ASTM D5185m	>20	1	2	
Water		WC Method	>.2	NEG	NEG	
Silt	scalar	*Visual	NONE	NONE	MODER	
Debris	scalar	*Visual	NONE	LIGHT	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	
Codium				•	0	
Sodium	ppm	ASTM D5185m	400	0	2	
Boron Barium	ppm	ASTM D5185m	400 200	312 0	284 0	
	ppm	ASTM D5185m ASTM D5185m		0 1		
Molybdenum	ppm		12	י <1	<1 5	
Manganese Magnesium	ppm	ASTM D5185m ASTM D5185m	12		6	
Calcium	ppm			4	33	
	ppm	ASTM D5185m	150	37		
Phosphorus	ppm	ASTM D5185m	1650	1708	1380	
Zinc Sulfur	ppm	ASTM D5185m	125	17	29	
Sullui	ppm	ASTM D5185m	22500	27253	24362	
Visc @ 40°C	cSt	ASTM D445	109	87.8	111	

Contact/Location: JAMIE FORESTER - FRAROCDC

# WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL







Contact/Location: JAMIE FORESTER - FRAROCDC Page 2 of 2