



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 644K 1DW644KZTED658665

Component
Diesel Engine

Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (28 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0217920	JR0199523	JR0172862
Sample Date		Client Info		17 May 2024	24 Jan 2024	05 May 2023
Machine Age	hrs	Client Info		13936	13381	12317
Oil Age	hrs	Client Info		555	1064	706
Filter Age	hrs	Client Info		555	0	706
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	19	29	12
Chromium	ppm	ASTM D5185m	>11	1	<1	<1
Nickel	ppm	ASTM D5185m	>5	<1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>31	5	5	4
Lead	ppm	ASTM D5185m	>26	2	7	2
Copper	ppm	ASTM D5185m	>26	2	2	<1
Tin	ppm	ASTM D5185m	>4	1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	9	8	6
Potassium	ppm	ASTM D5185m	>20	2	<1	2
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.8	1.7	0.8
Nitration	Abs/cm	*ASTM D7624	>20	8.3	9.0	7.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.2	24.9	20.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	<1	2	2
Boron	ppm	ASTM D5185m		237	172	185
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		230	242	231
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		863	950	860
Calcium	ppm	ASTM D5185m		1523	1570	1508
Phosphorus	ppm	ASTM D5185m		932	1012	896
Zinc	ppm	ASTM D5185m		1173	1265	1141
Sulfur	ppm	ASTM D5185m		3391	3310	3435
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.1	17.0	15.1
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.7	7.7	7.5
Visc @ 100°C	cSt	ASTM D445	15.4	14.2	14.9	14.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0217920
Lab Number : 06189955
Unique Number : 11046707
Test Package : CONST (Additional Tests: TBN)

Received : 23 May 2024
Tested : 25 May 2024
Diagnosed : 25 May 2024 - Wes Davis

JRE - MANASSAS PARK
 9107 OWENS DRIVE
 MANASSAS PARK, VA
 US 20111

Contact: DON VEST
 dvest@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (703)631-8500
 F: (703)631-4715