WEAR CONTAMINATION **FLUID CONDITION** **ABNORMAL** NORMAL **NORMAL**

Machine Id

FREIGHTLINER 514

Component

Diesel Engine

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		WC0905974		
No corrective action is recommended at this time. Resample at the next service interval to monitor.	Sample Date		Client Info		10 May 2024		
	Machine Age	mls	Client Info		84067		
	Oil Age	mls	Client Info		0		
	Filter Age	mls	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				ABNORMAL		
A/F A D			AOTM DEGOE				
WEAR	Iron	ppm	ASTM D5185m		<u>^</u> 90		
Cylinder, crank, or cam shaft wear is indicated.	Chromium	ppm	ASTM D5185m		<u>^</u> 8		
	Nickel	ppm	ASTM D5185m	>2	1		
	Titanium	ppm	ASTM D5185m	. 0	<1		
	Silver Aluminum	ppm	ASTM D5185m ASTM D5185m		<1 14		
	Lead	ppm	ASTM D5185m		14 2		
	Copper	ppm ppm	ASTM D5185m		3		
	Tin	ppm	ASTM D5185m		3 1		
	Vanadium	ppm	ASTM D5185m	70	- <1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	10		
There is no indication of any contamination in the cil	Potassium	ppm	ASTM D5185m	>20	14		
There is no indication of any contamination in the oil.	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	1.4		
	Nitration	Abs/cm	*ASTM D7624	>20	13.4		
	Sulfation	Abs/.1mm	*ASTM D7415		25.6		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>158	5		
	Boron	ppm	ASTM D5185m		4		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		71		
	Manganese	ppm	ASTM D5185m		1		
	Magnesium	ppm	ASTM D5185m	450	936		
	Calcium	ppm	ASTM D5185m		1308		
	Phosphorus	ppm	ASTM D5185m	1150	1043		
	Zinc	ppm	ASTM D5185m	1350	1328		
	Sulfur	ppm	ASTM D5185m	4250	3494		
	Oxidation	Abs/.1mm	*ASTM D7414		22.3		
	Base Number (BN)	mg KOH/g	ASTM D2896	8.5	6.3		
	Visc @ 100°C	cSt	ASTM D445		13.5		





Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0905974 Lab Number : 06189965

Test Package : MOB 1 (Additional Tests: TBN)

Received **Tested** Unique Number : 11046717 Diagnosed

: 23 May 2024 : 25 May 2024

: 29 May 2024 - Sean Felton

WAYNE CO SCHOOL BUS GARAGE 1603 SALEM CHURCH RD GOLDSBORO, NC US 27530

> Contact: BRANDON BRIGGS brandonbriggs@wcps.org T:

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: