



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Machine Id  
**913155**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (--- QTS)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0078301</b>	GFL0099260	GFL0099255
Sample Date		Client Info		<b>20 May 2024</b>	25 Apr 2024	13 Mar 2024
Machine Age	hrs	Client Info		<b>3101</b>	2933	3378
Oil Age	hrs	Client Info		<b>0</b>	0	0
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>Not Chngd</b>	Not Chngd	Not Chngd
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	<b>26</b>	9	28
Chromium	ppm	ASTM D5185m	>20	<b>&lt;1</b>	0	<1
Nickel	ppm	ASTM D5185m	>5	<b>&lt;1</b>	0	0
Titanium	ppm	ASTM D5185m	>2	<b>&lt;1</b>	0	0
Silver	ppm	ASTM D5185m	>2	<b>1</b>	0	<1
Aluminum	ppm	ASTM D5185m	>20	<b>11</b>	4	13
Lead	ppm	ASTM D5185m	>40	<b>&lt;1</b>	0	0
Copper	ppm	ASTM D5185m	>330	<b>3</b>	0	4
Tin	ppm	ASTM D5185m	>15	<b>1</b>	<1	<1
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>13</b>	4	8
Potassium	ppm	ASTM D5185m	>20	<b>23</b>	4	32
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>4	<b>0.6</b>	0.2	0.6
Nitration	Abs/cm	*ASTM D7624	>20	<b>11.4</b>	6.2	11.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>25.1</b>	18.2	24.7
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>1</b>	1	1
Boron	ppm	ASTM D5185m	0	<b>1</b>	6	5
Barium	ppm	ASTM D5185m	0	<b>0</b>	<1	0
Molybdenum	ppm	ASTM D5185m	60	<b>67</b>	63	61
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	0	<1
Magnesium	ppm	ASTM D5185m	1010	<b>961</b>	860	933
Calcium	ppm	ASTM D5185m	1070	<b>1120</b>	999	1066
Phosphorus	ppm	ASTM D5185m	1150	<b>958</b>	965	1010
Zinc	ppm	ASTM D5185m	1270	<b>1260</b>	1163	1254
Sulfur	ppm	ASTM D5185m	2060	<b>3061</b>	3351	3230
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>23.4</b>	14.3	20.9
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>6.0</b>	7.9	4.9
Visc @ 100°C	cSt	ASTM D445	15.4	<b>14.0</b>	13.6	14.2



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0078301  
**Lab Number** : 06190007  
**Unique Number** : 11046759  
**Test Package** : FLEET

**Received** : 23 May 2024  
**Tested** : 25 May 2024  
**Diagnosed** : 29 May 2024 - Don Baldrige

**GFL Environmental - 844 - Princeton Hauling**  
 10129 Highway 62 West  
 Princeton, KY  
 US 42445  
 Contact: ROBERT THIBAUT  
 robert.thibault@gflenv.com  
 T: (931)237-6045  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)