



PacLease

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
8591904
 Component
Diesel Engine
 Fluid
MOBIL DELVAC 1300 SUPER15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RPL0019804	RPL0016241	---
Sample Date		Client Info		09 May 2024	02 Apr 2024	---
Machine Age	mls	Client Info		15101	12533	---
Oil Age	mls	Client Info		0	0	---
Filter Age	mls	Client Info		0	0	---
Oil Changed		Client Info		Changed	Not Changed	---
Filter Changed		Client Info		Not Changed	Not Changed	---
Sample Status				NORMAL	NORMAL	---

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>100	142	112	---
Chromium	ppm	ASTM D5185m	>20	3	3	---
Nickel	ppm	ASTM D5185m	>4	1	0	---
Titanium	ppm	ASTM D5185m		<1	<1	---
Silver	ppm	ASTM D5185m	>3	<1	0	---
Aluminum	ppm	ASTM D5185m	>20	14	13	---
Lead	ppm	ASTM D5185m	>40	<1	0	---
Copper	ppm	ASTM D5185m	>330	37	40	---
Tin	ppm	ASTM D5185m	>15	2	1	---
Vanadium	ppm	ASTM D5185m		<1	0	---
White Metal	scalar	*Visual	NONE	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	---

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	35	37	---
Potassium	ppm	ASTM D5185m	>20	12	12	---
Fuel		WC Method	>5	<1.0	<1.0	---
Water		WC Method	>0.2	NEG	NEG	---
Glycol		WC Method		NEG	NEG	---
Soot %	%	*ASTM D7844	>3	1.4	1.2	---
Nitration	Abs/cm	*ASTM D7624	>20	11.3	10.6	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.6	25.1	---
Silt	scalar	*Visual	NONE	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		6	7	---
Boron	ppm	ASTM D5185m	0	148	182	---
Barium	ppm	ASTM D5185m	0	2	7	---
Molybdenum	ppm	ASTM D5185m	0	109	109	---
Manganese	ppm	ASTM D5185m		8	8	---
Magnesium	ppm	ASTM D5185m	0	677	677	---
Calcium	ppm	ASTM D5185m		1465	1444	---
Phosphorus	ppm	ASTM D5185m		627	662	---
Zinc	ppm	ASTM D5185m		837	802	---
Sulfur	ppm	ASTM D5185m		2517	2587	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.4	20.2	---
Base Number (BN)	mg KOH/g	ASTM D2896	9.4	7.1	7.2	---
Visc @ 100°C	cSt	ASTM D445	14	13.1	12.8	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RPL0019804
Lab Number : 06190207
Unique Number : 11046959
Test Package : FLEET

RTL PACLEASE - 7051 -Las Vegas
 4150 Arctic Spring Ave
 North Las Vegas, NV
 US 89115
 Contact: Rudy Trevizo
 TrevizoR@RushEnterprises.Com
 T: (702)208-7164
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)