

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

8465097

Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- QTS)

DIESEL ENGINE OIL SAE 15W40 (QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TESSIMETER/TION	Sample Number		Client Info		RPL0018141		
Resample at the next service interval to monitor.	Sample Date		Client Info		15 Apr 2024		
	Machine Age	mls	Client Info		0		
	Oil Age	mls	Client Info		17440		
	Filter Age	mls	Client Info		0		
	Oil Changed	0	Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status		Onorte into		NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>100	43		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	3		
	Nickel	ppm	ASTM D5185m	>4	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	>3	<1		
	Aluminum	ppm	ASTM D5185m	>20	10		
	Lead	ppm	ASTM D5185m		4		
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m		2		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		22		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	13		
	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.3		
	Nitration	Abs/cm	*ASTM D7624	>20	9.9		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	24.1		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		4		
The BN result indicates that there is suitable alkalinity remaining in the	Boron	ppm	ASTM D5185m		44		
oil. The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	100	57		
	Manganese	ppm	ASTM D5185m	1=6	1		
	Magnesium	ppm	ASTM D5185m		576		
	Calcium	ppm	ASTM D5185m		1608		
	Phosphorus	ppm	ASTM D5185m		711		
	Zinc	ppm	ASTM D5185m		938		
	Sulfur	ppm	ASTM D5185m		2826		
	Oxidation	Abs/.1mm	*ASTM D7414		26.0		
	Base Number (BN)		ASTM D2896		6.8		
	Visc @ 100°C	cSt	ASTM D445	14.4	13.1		







Certificate L2367

Laboratory Sample No.

: RPL0018141 Lab Number : 06190213 Unique Number : 11046965 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 24 May 2024 **Tested** : 29 May 2024

Diagnosed : 29 May 2024 - Sean Felton RTL PACLEASE - 7007 - Fontana 3121 South Riverside

Bloomington, CA US 92316

Contact: Rudy Trevizo TrevizoR@RushEnterprises.Com T: (909)829-1044

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)