

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

250

Component Diesel Engine

DIESEL ENGINE OIL SAE 40 (--- QTS)

DIESEL ENGINE OIL SAE 40 (Q13)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		WC0802048		
Resample at the next service interval to monitor. The fluid was not	Sample Date		Client Info		16 May 2024		
specified, however, a fluid match indicates that this fluid is (GENERIC) DIESEL ENGINE OIL SAE 40. Please confirm.	Machine Age	mls	Client Info		364895		
Please specify the component make and model with your next sample.	Oil Age	mls	Client Info		0		
r leade speelify the component make and model with your next sample.	Filter Age	mls	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR All component wear rates are normal.	Iron	ppm	ASTM D5185m		58		
	Chromium	ppm	ASTM D5185m		3		
	Nickel	ppm	ASTM D5185m	>4	1		
	Titanium	ppm	ASTM D5185m		8		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m		6		
	Lead	ppm	ASTM D5185m		5		
	Copper	ppm	ASTM D5185m		4		
	Tin	ppm	ASTM D5185m	>15	2		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ACTM DE10Em	. 05	44		
CONTAMINATION		ppm	ASTM D5185m		11 7		
There is no indication of any contamination in the oil.	Potassium Fuel	ppm	ASTM D5185m WC Method				
	Water		WC Method	>5	<1.0 NEG		
	Glycol		WC Method	>0.2	NEG		
	Soot %	%	*ASTM D7844	. 2	0.7		
	Nitration	Abs/cm	*ASTM D7624	>20	12.3		
	Sulfation	Abs/.1mm	*ASTM D7024		26.6		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>216	4		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m	250	50		
	Barium	ppm	ASTM D5185m	10	0		
	Molybdenum	ppm	ASTM D5185m	100	36		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m	450	384		
	Calcium	ppm	ASTM D5185m		2182		
	Phosphorus	ppm	ASTM D5185m		1022		
	Zinc	ppm	ASTM D5185m		1457		
	Sulfur	ppm	ASTM D5185m		3701		
	Oxidation	Abs/.1mm	*ASTM D7414		23.0		
	Base Number (BN)	0 0	ASTM D2896		6.5		
	Visc @ 100°C	cSt	ASTM D445	14.4	15.0		







Certificate L2367

Laboratory Sample No.

Lab Number : 06190253 Unique Number : 11047005 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0802048 Received : 24 May 2024 : 25 May 2024 **Tested**

Diagnosed : 25 May 2024 - Wes Davis 2801 MIDLAND BLVD. FORT SMITH, AR US 72904 Contact: RON BALL

rball@carcotrans.com T: (479)441-3228

CARCO TRANSPORTATION

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)