



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
4682M
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0122364	GFL0117625	GFL0108693
Sample Date		Client Info		22 May 2024	25 Apr 2024	23 Jan 2024
Machine Age	hrs	Client Info		16349	16154	14630
Oil Age	hrs	Client Info		15345	15345	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Not Chngd	Changed
Filter Changed		Client Info		Changed	Not Chngd	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>80	14	41	31
Chromium	ppm	ASTM D5185m	>5	1	3	1
Nickel	ppm	ASTM D5185m	>2	<1	0	<1
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>30	4	7	5
Lead	ppm	ASTM D5185m	>30	<1	<1	<1
Copper	ppm	ASTM D5185m	>150	1	0	3
Tin	ppm	ASTM D5185m	>5	1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	10	15	17
Potassium	ppm	ASTM D5185m	>20	2	<1	9
Fuel		WC Method	>5	<1.0	1.8	▲ 4.9
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.9	0.9
Nitration	Abs/cm	*ASTM D7624	>20	7.0	11.1	12.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.6	22.0	23.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	9	▲ 698
Boron	ppm	ASTM D5185m	0	0	<1	15
Barium	ppm	ASTM D5185m	0	0	0	<1
Molybdenum	ppm	ASTM D5185m	60	61	59	69
Manganese	ppm	ASTM D5185m	0	<1	<1	1
Magnesium	ppm	ASTM D5185m	1010	970	928	660
Calcium	ppm	ASTM D5185m	1070	1124	1057	771
Phosphorus	ppm	ASTM D5185m	1150	963	1040	741
Zinc	ppm	ASTM D5185m	1270	1288	1212	927
Sulfur	ppm	ASTM D5185m	2060	3294	3245	2064
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.1	19.4	20.3
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.5	7.4	5.7
Visc @ 100°C	cSt	ASTM D445	15.4	14.2	13.7	▲ 11.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0122364
Lab Number : 06190323
Unique Number : 11047075
Test Package : FLEET

GFL Environmental - 415 - Michigan East
 6200 Elmridge
 Sterling Heights, MI
 US 48313
 Contact: Frank Wolak
 fwolak@gflenv.com
 T: (586)825-9514
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)