



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>



Area  
**(BD08834)**  
Machine Id  
**212004**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0122508</b>	GFL0117703	GFL0105580
Sample Date		Client Info		<b>23 May 2024</b>	26 Mar 2024	20 Dec 2023
Machine Age	hrs	Client Info		<b>8505</b>	8023	7302
Oil Age	hrs	Client Info		<b>8023</b>	7302	0
Filter Age	hrs	Client Info		<b>8023</b>	7302	0
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>90	<b>36</b>	3	13
Chromium	ppm	ASTM D5185m	>20	<b>2</b>	<1	<1
Nickel	ppm	ASTM D5185m	>2	<b>&lt;1</b>	2	<1
Titanium	ppm	ASTM D5185m	>2	<b>&lt;1</b>	0	0
Silver	ppm	ASTM D5185m	>2	<b>&lt;1</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>4</b>	2	1
Lead	ppm	ASTM D5185m	>40	<b>1</b>	0	0
Copper	ppm	ASTM D5185m	>330	<b>2</b>	0	1
Tin	ppm	ASTM D5185m	>15	<b>1</b>	0	0
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>7</b>	3	4
Potassium	ppm	ASTM D5185m	>20	<b>2</b>	2	<1
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>6	<b>0.5</b>	0.3	0.6
Nitration	Abs/cm	*ASTM D7624	>20	<b>11.2</b>	5.9	8.0
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>23.3</b>	18.3	19.1
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>8</b>	2	2
Boron	ppm	ASTM D5185m	0	<b>0</b>	2	2
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	<1
Molybdenum	ppm	ASTM D5185m	60	<b>62</b>	52	59
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	0	<1
Magnesium	ppm	ASTM D5185m	1010	<b>996</b>	928	953
Calcium	ppm	ASTM D5185m	1070	<b>1127</b>	1041	1067
Phosphorus	ppm	ASTM D5185m	1150	<b>970</b>	1006	1111
Zinc	ppm	ASTM D5185m	1270	<b>1345</b>	1221	1284
Sulfur	ppm	ASTM D5185m	2060	<b>2928</b>	3421	2980
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>23.2</b>	14.3	15.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>6.1</b>	8.4	8.2
Visc @ 100°C	cSt	ASTM D445	15.4	<b>14.3</b>	14.2	13.7



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0122508  
**Lab Number** : 06190329  
**Unique Number** : 11047081  
**Test Package** : FLEET

**Received** : 24 May 2024  
**Tested** : 29 May 2024  
**Diagnosed** : 29 May 2024 - Don Baldrige

**GFL Environmental - 415 - Michigan East**  
 6200 Elmridge  
 Sterling Heights, MI  
 US 48313  
 Contact: Frank Wolak  
 fwolak@gflenv.com  
 T: (586)825-9514  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)