
**WEAR CONTAMINATION FLUID CONDITION**  **NORMAL NORMAL NORMAL** 

[702776 ANSBRO]

VOLVO EC300EL 317276

**Swing Drive** 

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP447293		
	Sample Date		Client Info		25 Apr 2024		
	Machine Age	hrs	Client Info		1109		
	Oil Age	hrs	Client Info		500		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		None		
	Sample Status				NORMAL		
VEAR	Iron	ppm	ASTM D5185m	>400	152		
	Chromium	ppm	ASTM D5185m		2		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m	>10	0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		11		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		12		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		<1		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	111	155		
	Barium	ppm	ASTM D5185m	0.0	0		
	Molybdenum	ppm	ASTM D5185m	0.9	5		
	Manganese	ppm	ASTM D5185m	0.0	2		
	Magnesium	ppm	ASTM D5185m	39	38		
	Calcium	ppm	ASTM D5185m	93	149		
	Phosphorus	ppm	ASTM D5185m	920	937		
	Zinc	ppm	ASTM D5185m	104	95		
	Sulfur	ppm	ASTM D5185m	20179	31304		
	Visc @ 40°C	cSt	ASTM D445	333	249		





Certificate L2367

Report Id: VOLVO0093 [WUSCAR] 06190778 (Generated: 05/28/2024 07:54:44) Rev: 1

Laboratory Sample No.

: VCP447293 Lab Number : 06190778 Unique Number : 11047530 Test Package : MOB 1

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 24 May 2024

**Tested** : 28 May 2024 : 28 May 2024 - Wes Davis Diagnosed

ALTA EQUIPMENT/FLAGLER CONSTRUCTION EQUIPMENT LLC

8418 PALM RIVER ROAD

TAMPA, FL US 33619

Contact: JOHN FARDELLA

john.fardella@altg.com T: (813)630-0077

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (813)630-2233