WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL





## VOLVO L70H 622411


Front Axle

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info	2.1111071011	ML0001565		
	Sample Date		Client Info		17 May 2024		
	Machine Age	hrs	Client Info		11424		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
A/CAD							
WEAR	Iron	ppm	ASTM D5185m		79		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		1		
	Nickel	ppm	ASTM D5185m	>10	1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	00	<1		
	Aluminum	ppm	ASTM D5185m		1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m	>20	0		
	White Metal	ppm scalar	ASTM D5185m *Visual	NONE	<1 NONE		
	Yellow Metal		*Visual	NONE	NONE		
	Tellow Metal	scalar	Visuai	INOINL	HONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	14		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	LIGHT		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		7		
	Boron	ppm	ASTM D5185m		116		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		9		
	Manganese	ppm	ASTM D5185m		3		
	Magnesium	ppm	ASTM D5185m		50		
	Calcium	ppm	ASTM D5185m		3545		
	Phosphorus	ppm	ASTM D5185m		1180		
	Zinc	ppm	ASTM D5185m		1446		
	Sulfur	ppm	ASTM D5185m		8515		
	Visc @ 40°C	cSt	ASTM D445		48.4		











Certificate L2367

Laboratory Sample No.

: ML0001565 Lab Number : 06190814 Unique Number : 11047566 Test Package : CONST

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 24 May 2024 **Tested** : 29 May 2024

Diagnosed

: 29 May 2024 - Sean Felton

PO BOX 600 CHANTILLY, VA US 20153 Contact: SERVICE MANAGER

**WILLIAM HAZEL** 

jimmy\_elswick@wahazel.com T: (703)378-8300

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: