

Area



VOLVO A30F 82256 {not provided} (11 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample. (Customer Sample Comment: W02008336)

WEAR

All component wear rates are normal.

CONTAMINATION

There is no indication of any contamination in the oil.

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ML0002462		
Sample Date		Client Info		21 May 2024		
Machine Age	hrs	Client Info		14598		
Oil Age	hrs	Client Info		2000		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		N/A		
Sample Status				NORMAL		
Iron	ppm	ASTM D5185m	>630	206		
Chromium	ppm	ASTM D5185m	>15	2		
Nickel	ppm	ASTM D5185m	>8	2		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>10	0		
Lead	ppm	ASTM D5185m	>4	0		
Copper	ppm	ASTM D5185m	>50	8		
Tin	ppm	ASTM D5185m	>4	<1		
Vanadium	ppm	ASTM D5185m		0		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
0				_		
Silicon	ppm	ASTM D5185m	>50	5		
Potassium Water	ppm	ASTM D5185m WC Method	>20	<1 NEG		
Silt	agalar		>0.2 NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar scalar	*Visual *Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
			20.2			
Sodium	ppm	ASTM D5185m		<1		
Boron	ppm	ASTM D5185m		179		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		3		
Manganese	ppm	ASTM D5185m		4		
Magnesium	ppm	ASTM D5185m		16		
Calcium	ppm	ASTM D5185m		283		
Phosphorus	ppm	ASTM D5185m		1087		
Zinc	ppm	ASTM D5185m		165		
Sulfur	ppm	ASTM D5185m		29585		
V/ 0 4000	- 01			0.47		

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL


Visc @ 40°C

cSt

ASTM D445

Submitted By: DARRELL ANDES

247



Ferrous Alloys 220 20 ickel 180 160 140 120 mdo 100 80 40 20 0 May21/24 Non-ferrous Metals 10 n lead maa 1 CVEV Viscosity @ 40°C 250 240 230 220 210 200 190 180 (j. 170 0-0+ 160 ਲੋਂ ₁₅₀ 140 130 Ab 120 110 100-90 Ab 80 70 Mav21/24 May21/24

: WearCheck USA - 501 Madison Ave., Cary, NC 27513



: ML0002462 Received : 24 May 2024 8450 QUARRY ROAD Tested : 29 May 2024 MANASSAS, VA Diagnosed : 29 May 2024 - Sean Felton US 20110 Contact: MIKE MAYHUGH MMAYHUGH@MCCLUNG-LOGAN.COM To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (703)393-7344 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (703)393-7844

Certificate L2367

Laboratory

Sample No.

Lab Number : 06190817

Unique Number : 11047569

Test Package : CONST

Submitted By: DARRELL ANDES Page 2 of 2

MCCLUNG-LOGAN EQUIPMENT CO - MANASSAS