WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Area


[W02008336]


VOLVO A30F 82256


Rear Axle


Fluid {not provided} (11 GAL)

{not provided} (11 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample. (Customer Sample Comment: W02008336)	Sample Number		Client Info		ML0002466		
	Sample Date		Client Info		21 May 2024		
	Machine Age	hrs	Client Info		14598		
	Oil Age	hrs	Client Info		2000		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>630	280		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		3		
	Nickel	ppm	ASTM D5185m		2		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>10	<1		
	Lead	ppm	ASTM D5185m	>4	0		
	Copper	ppm	ASTM D5185m	>50	6		
	Tin	ppm	ASTM D5185m	>4	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>50	6		
	Potassium	ppm	ASTM D5185m		2		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	LIGHT		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		218		
The condition of the off is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		3		
	Manganese	ppm	ASTM D5185m		5		
	Magnesium	ppm	ASTM D5185m		16		
	Calcium	ppm	ASTM D5185m		217		
	Phosphorus	ppm	ASTM D5185m		1100		
	Zinc	ppm	ASTM D5185m		140		
	Sulfur	ppm	ASTM D5185m		30040		
	Visc @ 40°C	cSt	ASTM D445		250		











Certificate L2367

Laboratory Sample No.

: ML0002466 Lab Number : 06190820 Unique Number : 11047572 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 24 May 2024 **Tested** : 29 May 2024

: 29 May 2024 - Sean Felton

MCCLUNG-LOGAN EQUIPMENT CO - MANASSAS 8450 QUARRY ROAD

MANASSAS, VA US 20110

Contact: MIKE MAYHUGH

MMAYHUGH@MCCLUNG-LOGAN.COM To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (703)393-7344

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Diagnosed

F: (703)393-7844