



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area  
**FRANK JOHNSON**  
Machine Id  
**[FRANK JOHNSON] 002 298198-2**  
Component  
**Center Main Engine**  
Fluid  
**CHEVRON DELO 710 LS (350 GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>MW0068279</b>	MW0065691	MW0068008
Sample Date		Client Info		<b>01 May 2024</b>	01 Apr 2024	01 Mar 2024
Machine Age	hrs	Client Info		<b>4848</b>	4184	3413
Oil Age	hrs	Client Info		<b>4848</b>	0	279
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>N/A</b>	N/A	N/A
Filter Changed		Client Info		<b>N/A</b>	N/A	N/A
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	<b>12</b>	10	11
Chromium	ppm	ASTM D5185m	>8	<b>2</b>	2	2
Nickel	ppm	ASTM D5185m	>2	<b>&lt;1</b>	0	0
Titanium	ppm	ASTM D5185m	>3	<b>&lt;1</b>	0	<1
Silver	ppm	ASTM D5185m	>2	<b>1</b>	0	0
Aluminum	ppm	ASTM D5185m	>15	<b>2</b>	2	1
Lead	ppm	ASTM D5185m	>18	<b>7</b>	8	7
Copper	ppm	ASTM D5185m	>80	<b>10</b>	8	8
Tin	ppm	ASTM D5185m	>14	<b>8</b>	8	8
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>20	<b>5</b>	3	4
Potassium	ppm	ASTM D5185m	>20	<b>3</b>	0	0
Fuel		WC Method	>4.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844		<b>0.3</b>	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	<b>8.5</b>	8.6	8.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>16.2</b>	16.7	16.1
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	<b>1</b>	0	<1
Boron	ppm	ASTM D5185m		<b>46</b>	41	40
Barium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
Molybdenum	ppm	ASTM D5185m		<b>50</b>	52	46
Manganese	ppm	ASTM D5185m		<b>2</b>	1	1
Magnesium	ppm	ASTM D5185m		<b>16</b>	16	5
Calcium	ppm	ASTM D5185m		<b>3756</b>	4174	3649
Phosphorus	ppm	ASTM D5185m		<b>21</b>	11	3
Zinc	ppm	ASTM D5185m		<b>15</b>	13	<1
Sulfur	ppm	ASTM D5185m		<b>2628</b>	3186	2805
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>8.8</b>	9.1	8.7
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	<b>9.36</b>	10.09	9.69
Visc @ 100°C	cSt	ASTM D445	15.5	<b>14.1</b>	14.2	14.0


**FT-IR (Direct Trend)**




**Base Number**




**Viscosity @ 100°C**




**Ferrous Alloys**




**Non-ferrous Metals**



**Viscosity @ 100°C**



**Base Number**



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513

**Sample No.** : MW0068279

**Lab Number** : 06191226

**Unique Number** : 11047978

**Test Package** : MAR 2

**Received** : 24 May 2024

**Tested** : 29 May 2024

**Diagnosed** : 29 May 2024 - Don Baldrige

**INGRAM BARGE**

900 S 3RD ST

PADUCAH, KY

US 42003

Contact: GLENN ELLIS

glenn.ellis@ingrambarga.com

T: (270)415-4467

F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)