



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
EPIROC T35-12 JPS22SED2701
 Component
Compressor
 Fluid
PAR OIL (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0212660	JR0197481	JR0197683
Sample Date		Client Info		21 May 2024	21 Mar 2024	23 Jan 2024
Machine Age	hrs	Client Info		2384	2023	1740
Oil Age	hrs	Client Info		2384	1399	624
Filter Age	hrs	Client Info		361	0	0
Oil Changed		Client Info		Not Chngd	Changed	Not Chngd
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184		17	12	9
Iron	ppm	ASTM D5185m	>50	3	0	2
Chromium	ppm	ASTM D5185m	>5	<1	0	<1
Nickel	ppm	ASTM D5185m		<1	<1	<1
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m		1	0	0
Aluminum	ppm	ASTM D5185m	>15	1	<1	3
Lead	ppm	ASTM D5185m	>65	<1	<1	<1
Copper	ppm	ASTM D5185m	>65	1	<1	1
Tin	ppm	ASTM D5185m	>10	<1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>35	2	1	<1
Potassium	ppm	ASTM D5185m	>20	2	2	3
Water		WC Method	>0.1	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		4	7	13
Boron	ppm	ASTM D5185m		4	0	0
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		6	0	<1
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		22	10	7
Calcium	ppm	ASTM D5185m		102	30	16
Phosphorus	ppm	ASTM D5185m		273	243	161
Zinc	ppm	ASTM D5185m		287	245	179
Sulfur	ppm	ASTM D5185m		6133	5901	5212
Visc @ 40°C	cSt	ASTM D445		47.6	46.2	46.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0212660 **Received** : 24 May 2024
Lab Number : 06191251 **Tested** : 29 May 2024
Unique Number : 11048003 **Diagnosed** : 29 May 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

CAROLINA CIVIL
 PO BOX 80337
 RALEIGH, NC
 US 27623
 Contact:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: