WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL ATTENTION


Ascendum Machinery/250 Hour Service


SANDVIK 56875


Rear Left Final Drive

Test UOM Method Limit/Abn Current History1 Hi	History2
at Sample Number Client Info ASC0009559 ASC0005254 VC	VCP00065
	09 May 20
Machine AgehrsClient Info9895896980	8043
Oil Age hrs Client Info 926 926 92	920
Filter Age hrs Client Info 0 0	0
Oil Changed Client Info Changed Changed Ch	Changed
Filter Changed Client Info N/A N/A N/A	N/A
Sample Status ATTENTION AT	ATTENTIC
Iron ppm ASTM D5185m >500 215 0	131
Chromium ppm ASTM D5185m >10 <1 0	<1
Nickel ppm ASTM D5185m >10 0 0	1
Titanium ppm ASTM D5185m <1 0	<1
Silver ppm ASTM D5185m 0 0	0
Aluminum ppm ASTM D5185m >25 8 0	8
Lead ppm ASTM D5185m >25 6 0	5
Copper ppm ASTM D5185m >50 13 <1	4
Tin ppm ASTM D5185m >10 <1 0	0
VanadiumppmASTM D5185m00	<1
White Metal scalar *Visual NONE NONE NONE	MODE
Yellow Metal scalar *Visual NONE NONE NONE	NONE
Silicon ppm ASTM D5185m >75 29 <1	13
Potassium ppm ASTM D5185m >20 0 0	2
Water WC Method >0.2 NEG NEG	NEG
Silt scalar *Visual NONE NONE NONE	NONE
Debris scalar *Visual NONE NONE NONE	NONE
Sand/Dirt scalar *Visual NONE NONE NONE	NONE
Appearance scalar *Visual NORML NORML NORML	NORM
Odor scalar *Visual NORML NORML NORML	NORM
Emulsified Water scalar *Visual >0.2 NEG NEG	NEG
Sodium ppm ASTM D5185m 4 0	<1
Boron ppm ASTM D5185m 379 219 191	190
Barium ppm ASTM D5185m 0.0 <1 0	0
Molybdenum ppm ASTM D5185m 0.8 2 0	<1
Manganese ppm ASTM D5185m 0.0 2 0	1
MagnesiumppmASTM D5185m31<12	<1
Calcium ppm ASTM D5185m 38 100 149	23
Phosphorus ppm ASTM D5185m 1077 1168 1025	1053
Zinc ppm ASTM D5185m 46 73 55	9
Sulfur ppm ASTM D5185m 23526 32989 27848	33502
Sulfur ppm ASTM D5185m 23526 32989 27848 Visc @ 40°C cSt ASTM D445 139 236 309	









Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)



Certificate L2367

Laboratory Sample No.

: ASC0009559 Lab Number : 06191386 Unique Number : 11048138

Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 24 May 2024 **Tested** : 29 May 2024

Diagnosed : 29 May 2024 - Sean Felton

4551 BEATTIES FORD ROAD CHARLOTTE, NC

US 28216 Contact: TIM BYLES

MARTIN MARIETTA

tim.byles@martinmarrietta.com T: (704)392-1333

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Submitted By: CLAYTON SMITH

F: