



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 655K 1T0655KXEEE272750
 Component
Diesel Engine
 Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (30 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0210762	JRMC462472	---
Sample Date		Client Info		22 May 2024	09 Oct 2018	---
Machine Age	hrs	Client Info		2380	1776	---
Oil Age	hrs	Client Info		1776	0	---
Filter Age	hrs	Client Info		1776	0	---
Oil Changed		Client Info		Changed	Changed	---
Filter Changed		Client Info		Changed	Changed	---
Sample Status				NORMAL	NORMAL	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>149	68	18	---
Chromium	ppm	ASTM D5185m	>11	1	<1	---
Nickel	ppm	ASTM D5185m	>5	2	<1	---
Titanium	ppm	ASTM D5185m		<1	0	---
Silver	ppm	ASTM D5185m	>3	<1	0	---
Aluminum	ppm	ASTM D5185m	>31	6	1	---
Lead	ppm	ASTM D5185m	>26	<1	<1	---
Copper	ppm	ASTM D5185m	>26	11	3	---
Tin	ppm	ASTM D5185m	>4	<1	0	---
Vanadium	ppm	ASTM D5185m		<1	0	---
White Metal	scalar	*Visual	NONE	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	---

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>50	12	3	---
Potassium	ppm	ASTM D5185m	>20	12	19	---
Fuel		WC Method	>2.1	<1.0	<1.0	---
Water		WC Method	>0.21	NEG	NEG	---
Glycol		WC Method		NEG	NEG	---
Soot %	%	*ASTM D7844	>3	0.8	0.3	---
Nitration	Abs/cm	*ASTM D7624	>20	10.6	7.6	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	27.0	20.4	---
Silt	scalar	*Visual	NONE	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	9	5	---
Boron	ppm	ASTM D5185m		105	31	---
Barium	ppm	ASTM D5185m		0	0	---
Molybdenum	ppm	ASTM D5185m		238	2	---
Manganese	ppm	ASTM D5185m		1	2	---
Magnesium	ppm	ASTM D5185m		777	12	---
Calcium	ppm	ASTM D5185m		1733	2448	---
Phosphorus	ppm	ASTM D5185m		921	830	---
Zinc	ppm	ASTM D5185m		1144	1018	---
Sulfur	ppm	ASTM D5185m		3612	2940	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.8	17.6	---
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	7.3	8.7	---
Visc @ 100°C	cSt	ASTM D445	15.4	15.0	15.27	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : JR0210762

Lab Number : 06191480

Unique Number : 11048232

Test Package : CONST (Additional Tests: TBN)

Received : 24 May 2024

Tested : 29 May 2024

Diagnosed : 29 May 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - STEPHENSON

245 YARDMASTER COURT

STEPHENSON, VA

US 22656-1761

Contact: PHIL DAUGHERTY

pdaugherty@jamesriverequipment.com

T: x:

F: (540)693-2588