WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**


Machine Id

PETERBILT 496480

Diesel Engine

CITGO CITGUARD 600 15W40 (48 QTS)

| DECOMMENDATION. | - . | | | | | L | |
|--|---------------------------------------|----------|-------------|-----------|-------------|----------|----------|
| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
| Resample at the next service interval to monitor. | Sample Number | | Client Info | | RPL0004350 | | |
| | Sample Date | | Client Info | | 13 May 2024 | | |
| | Machine Age | mls | Client Info | | 393121 | | |
| | Oil Age | mls | Client Info | | 22998 | | |
| | Filter Age | mls | Client Info | | 22998 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | Not Changd | | |
| | Sample Status | | | | NORMAL | | |
| WEAR | Iron | ppm | ASTM D5185m | >165 | 15 | | |
| | Chromium | ppm | ASTM D5185m | | 1 | | |
| All component wear rates are normal. | Nickel | ppm | ASTM D5185m | | - <1 | | |
| | Titanium | ppm | ASTM D5185m | | <1 | | |
| | Silver | ppm | ASTM D5185m | | 1 | | |
| | Aluminum | ppm | ASTM D5185m | | 3 | | |
| | Lead | ppm | ASTM D5185m | | 2 | | |
| | Copper | ppm | ASTM D5185m | | 1 | | |
| | Tin | ppm | ASTM D5185m | | 1 | | |
| | Vanadium | ppm | ASTM D5185m | 70 | <1 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| | · · · · · · · · · · · · · · · · · · · | | VIOUUI | | | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >35 | 6 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185m | >20 | 5 | | |
| | Fuel | | WC Method | >3.0 | <1.0 | | |
| | Water | | WC Method | >0.2 | NEG | | |
| | Glycol | | WC Method | | NEG | | |
| | Soot % | % | *ASTM D7844 | >7.5 | 0.4 | | |
| | Nitration | Abs/cm | *ASTM D7624 | >20 | 9.4 | | |
| | Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 21.5 | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.2 | NEG | | |
| THUR CONDITION | | | | | | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | | <1 | | |
| The BN result indicates that there is suitable alkalinity remaining in the | Boron | ppm | ASTM D5185m | | 1 | | |
| oil. The condition of the oil is suitable for further service. | Barium | ppm | ASTM D5185m | | 1 | | |
| | Molybdenum | ppm | ASTM D5185m | 57 | 64 | | |
| | Manganese | ppm | ASTM D5185m | | <1 | | |
| | Magnesium | ppm | ASTM D5185m | | 515 | | |
| | Calcium | ppm | ASTM D5185m | | 1689 | | |
| | Phosphorus | ppm | ASTM D5185m | | 1147 | | |
| | Zinc | ppm | | 1089 | 1315 | | |
| | Sulfur | ppm | ASTM D5185m | | 3598 | | |
| | Oxidation | Abs/.1mm | *ASTM D7414 | | 17.4 | | |
| | Base Number (BN) | 0 0 | ASTM D2896 | 11.0 | 7.9 | | |
| | Visc @ 100°C | cSt | ASTM D445 | 15.4 | 12.9 | | |







Certificate L2367

Laboratory Sample No.

: RPL0004350 Lab Number : 06192058 Unique Number : 11048810 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 28 May 2024 **Tested** : 29 May 2024

Diagnosed : 29 May 2024 - Wes Davis 8109 East Adamo Drive Tampa, FL US 33619

Contact: Michael Reid REIDM@RushEnterprises.com T: (813)371-2130

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)