



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
[W51961 HENDERSON]

Machine Id
JOHN DEERE 135G 1FF135GXHJF500840

Component
Hydraulic System

Fluid
HITACHI HYDRAULIC SUPER EX 46HN (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0211650	JR0180012	JR0147221
Sample Date		Client Info		23 May 2024	11 Sep 2023	05 Jan 2023
Machine Age	hrs	Client Info		3936	3454	2944
Oil Age	hrs	Client Info		0	0	2944
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Not Changd	Not Changd
Filter Changed		Client Info		Changed	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	16	10	11
Iron	ppm	ASTM D5185m	>32	16	18	14
Chromium	ppm	ASTM D5185m	>9	0	0	<1
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>9	<1	2	<1
Lead	ppm	ASTM D5185m	>28	0	0	0
Copper	ppm	ASTM D5185m	>50	0	<1	<1
Tin	ppm	ASTM D5185m	>5	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>11	3	2	2
Potassium	ppm	ASTM D5185m	>20	1	1	<1
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	6406	14332	27327
Particles >6µm		ASTM D7647	>20000	552	5349	6266
Particles >14µm		ASTM D7647	>640	36	400	168
Particles >21µm		ASTM D7647	>160	8	57	25
Particles >38µm		ASTM D7647	>40	0	0	0
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	20/16/12	21/20/16	22/20/15
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	2	3	2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		1	0	<1
Calcium	ppm	ASTM D5185m		21	28	28
Phosphorus	ppm	ASTM D5185m	827	437	483	447
Zinc	ppm	ASTM D5185m	0	65	68	69
Sulfur	ppm	ASTM D5185m	13	137	226	203
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.16	0.17	0.11
Visc @ 40°C	cSt	ASTM D445	47	45.5	46.1	45.9



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0211650 **Received** : 28 May 2024
Lab Number : 06192092 **Tested** : 29 May 2024
Unique Number : 11048844 **Diagnosed** : 30 May 2024 - Angela Borella
Test Package : CONST (Additional Tests: PQ)

JRE - ASHLAND
 11047 LEADBETTER RD
 ASHLAND, VA
 US 23005
 Contact: DAVID ZIEG
 dzieg@jamesriverequipment.com
 T: (804)798-6001
 F: (804)798-0292

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)