WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

JOHN DEERE 460P 1DW460PATPFB06235

Hydraulic System

JOHN DEERE HYDRAU (--- GAL)

	Toot	11014	1 / a + b = -l	Limit/Alex	A	I lintom d	I lieta e O
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		WE0007321		
	Sample Date	la con	Client Info		23 May 2024		
	Machine Age	hrs	Client Info		1917		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR All component wear rates are normal.	PQ		ASTM D8184		14		
	Iron	ppm	ASTM D5185m	>20	1		
	Chromium		ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	>10			
	Silver	ppm	ASTM D5185m		<1		
		ppm		×10	0		
	Aluminum Lead	ppm	ASTM D5185m		0		
		ppm	ASTM D5185m		-		
	Copper	ppm	ASTM D5185m		<1 0		
		ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m	NONE	-		
	White Metal	scalar	*Visual		NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.	Silicon	ppm	ASTM D5185m	>20	1		
	Potassium	ppm	ASTM D5185m		2		
	Water	ррпп	WC Method		NEG		
	Particles >4µm		ASTM D7647		3114		
	Particles >6µm		ASTM D7647		898		
	Particles >14µm		ASTM D7647		84		
	Particles >21µm		ASTM D7647		20		
	Particles >38µm		ASTM D7647		0		
	Particles >30µm		ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		19/17/14		
	Silt	000101	*Visual		NONE		
	Debris	scalar		NONE			
	Sand/Dirt	scalar	*Visual	NONE	NONE		
		scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML NEG		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		1		
TEGID CONDITION	Boron	ppm	ASTM D5185m		0		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		3		
	Calcium	ppm	ASTM D5185m	87	225		
	Phosphorus	ppm	ASTM D5185m		649		
	Zinc	ppm	ASTM D5185m		824		
	Sulfur	ppm	ASTM D5185m		1903		
	Acid Number (AN)	mg KOH/g	ASTM D3103111		0.59		
	ACIG NUMBER (AIN)	my Normy		65	0.55	_	





Certificate L2367

Laboratory Sample No.

: WE0007321 Lab Number : 06192101

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

Tested Unique Number : 11048853 Diagnosed Test Package : CONST (Additional Tests: PQ)

: 29 May 2024

: 29 May 2024 - Wes Davis

: 28 May 2024

4308 WATER TRAIL GRAYSVILLE, AL US 35073 Contact: BEN BYRKET

bbyrket@warriortractor.com

WARRIOR TRACTOR AND EQUIPMENT - GRAYSVILLE

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (205)675-9045 F: Contact/Location: BEN BYRKET - WARGRAAL