WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


[W51902]

JOHN DEERE 350P 1FF350PAKPF000789

Left Final Drive

JOHN DEERE GL-5 80W90 (--- GAL)

| OHN DEERE GL-5 80W90 (GAL) | | | | | | | |
|---|------------------|--------|-------------|-----------|-------------|----------|---------|
| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History |
| Resample at the next service interval to monitor. | Sample Number | | Client Info | | JR0212361 | | |
| | Sample Date | | Client Info | | 22 May 2024 | | |
| | Machine Age | hrs | Client Info | | 513 | | |
| | Oil Age | hrs | Client Info | | 0 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Not Changd | | |
| | Filter Changed | | Client Info | | N/A | | |
| | Sample Status | | | | NORMAL | | |
| VEAR | PQ | | ASTM D8184 | >1250 | 76 | | |
| | Iron | ppm | ASTM D5185m | >750 | 356 | | |
| All component wear rates are normal. | Chromium | ppm | ASTM D5185m | | 5 | | |
| | Nickel | ppm | ASTM D5185m | | <1 | | |
| | Titanium | ppm | ASTM D5185m | | <1 | | |
| | Silver | ppm | ASTM D5185m | | <1 | | -, |
| | Aluminum | ppm | ASTM D5185m | >40 | 1 | | |
| | Lead | ppm | ASTM D5185m | >15 | <1 | | |
| | Copper | ppm | ASTM D5185m | >40 | 1 | | |
| | Tin | ppm | ASTM D5185m | >10 | 0 | | |
| | Vanadium | ppm | ASTM D5185m | | <1 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| | | | | | | | |
| ONTAMINATION | Silicon | ppm | ASTM D5185m | | 15 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185m | | 2 | | |
| | Water | | WC Method | >0.075 | NEG | | |
| | Silt | scalar | *Visual | NONE | MODER | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >0.075 | NEG | | |
| LUID CONDITION | Sodium | ppm | ASTM D5185m | >51 | 2 | | |
| The condition of the oil is acceptable for the time in service. | Boron | ppm | ASTM D5185m | | 62 | | |
| | Barium | ppm | ASTM D5185m | | <1 | | |
| | Molybdenum | ppm | ASTM D5185m | | <1 | | |
| | Manganese | ppm | ASTM D5185m | | 7 | | |
| | Magnesium | ppm | ASTM D5185m | | 2 | | |
| | Calcium | ppm | ASTM D5185m | | 23 | | |
| | Phosphorus | ppm | ASTM D5185m | | 482 | | |
| | Zinc | ppm | ASTM D5185m | | 16 | | |
| | Sulfur | ppm | ASTM D5185m | | 14941 | | |
| | Visc @ 40°C | cSt | ASTM D445 | | 187 | | |





Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Lab Number : 06192491 Unique Number : 11049243 Test Package : CONST (Additional Tests: PQ)

: JR0212361

Received **Tested** Diagnosed

: 28 May 2024 : 30 May 2024

: 30 May 2024 - Sean Felton

JRE - ASHLAND 11047 LEADBETTER RD ASHLAND, VA US 23005

Contact: DAVID ZIEG dzieg@jamesriverequipment.com T: (804)798-6001

Contact/Location: DAVID ZIEG - JAMASH

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (804)798-0292