
WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

[A12575] VOLVO L120H 633530

Front Axle

MOBIL WB 102 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP416931		
	Sample Date		Client Info		22 May 2024		
	Machine Age	hrs	Client Info		1000		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>500	73		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	2		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		2		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>30	2		
	Lead	ppm	ASTM D5185m	>50	0		
	Copper	ppm	ASTM D5185m	>120	<1		
	Tin	ppm	ASTM D5185m	>20	0		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ASTM D5185m	. 50	24		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		3		
	Water	ppiii	WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		179		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		10		
	Manganese	ppm	ASTM D5185m		4		
	Magnesium	ppm	ASTM D5185m		129		
	Calcium	ppm	ASTM D5185m		5109		
	Phosphorus	ppm	ASTM D5185m		1701		
	Zinc	ppm	ASTM D5185m		2155		
	Sulfur	ppm	ASTM D5185m		6548		
	Visc @ 40°C	cSt	ASTM D445		43.9		





Certificate L2367

Report Id: GOUAVO [WUSCAR] 06192574 (Generated: 05/30/2024 17:29:46) Rev: 1

Laboratory Sample No.

: VCP416931 Lab Number : 06192574 Unique Number : 11049326 Test Package : MOB 1

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 28 May 2024 **Tested** : 29 May 2024

: 30 May 2024 - Don Baldridge Diagnosed

GOURMETS DELIGHT PO BOX 160

AVONDALE, PA US 19311

Contact: GABE VALENTINO

gabe.valentino@gourmetsfinest.com T: (610)268-3578

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (610)268-2298