

WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL NORMAL

Machine Id

## 24E2007 HL-031

New (Unused) Oil

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
This is a baseline read-out on the submitted sample.	Sample Number		Client Info		HPL0004935		
	Sample Date		Client Info		21 May 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
VEAR	Iron	nnm	ASTM D5185m		0		
WLAN	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION							
	Silicon	ppm	ASTM D5185m		2		
	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
<u></u>	Emulsified Water	scalar	*Visual		NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2		
	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		2		
	Calcium	ppm	ASTM D5185m		64		
	Phosphorus	ppm	ASTM D5185m		357		
	Zinc	ppm	ASTM D5185m		417		
	Sulfur	ppm	ASTM D5185m		5306		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.50		
	Visc @ 40°C Visc @ 100°C	cSt	ASTM D445		110.3		
		cSt	ASTM D445		13.89		





Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : HPL0004935 Lab Number : 06192651

Unique Number : 11049403

Received : 28 May 2024 **Tested** Diagnosed

: 31 May 2024 : 31 May 2024 - Jonathan Hester

HIGH PERFORMANCE LUBRICANTS LLC 500 S SPRUCE ST

MANTENO, IL US 60950 Contact: DAVID WARD

Test Package : MOB 2 ( Additional Tests: FT-IR, ICP-NewOil, KV100, PrtCount, VI ) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

sampledata@hplubricants.com T: (815)468-3535

Submitted By: DAVID WARD

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: x: