



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
24E2204 BAPSR-305
 Component
New (Unused) Oil
 Fluid
Gasoline Engine Oil (--- GAL)

RECOMMENDATION

This is a baseline read-out on the submitted sample. (Customer Sample Comment: RUN TBN)

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		HPL0004354	---	---
Sample Date		Client Info		22 May 2024	---	---
Machine Age	hrs	Client Info		0	---	---
Oil Age	hrs	Client Info		0	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		Not Changd	---	---
Filter Changed		Client Info		N/A	---	---
Sample Status				NORMAL	---	---

WEAR









Iron	ppm	ASTM D5185m		0	---	---
Chromium	ppm	ASTM D5185m		0	---	---
Nickel	ppm	ASTM D5185m		0	---	---
Titanium	ppm	ASTM D5185m		0	---	---
Silver	ppm	ASTM D5185m		0	---	---
Aluminum	ppm	ASTM D5185m		14	---	---
Lead	ppm	ASTM D5185m		<1	---	---
Copper	ppm	ASTM D5185m		0	---	---
Tin	ppm	ASTM D5185m		<1	---	---
Vanadium	ppm	ASTM D5185m		<1	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

CONTAMINATION

Silicon	ppm	ASTM D5185m		28	---	---
Potassium	ppm	ASTM D5185m	>20	2	---	---
Water		WC Method		NEG	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual		NEG	---	---

FLUID CONDITION

Sodium	ppm	ASTM D5185m		16	---	---
Boron	ppm	ASTM D5185m		203	---	---
Barium	ppm	ASTM D5185m		3	---	---
Molybdenum	ppm	ASTM D5185m		1051	---	---
Manganese	ppm	ASTM D5185m		<1	---	---
Magnesium	ppm	ASTM D5185m		534	---	---
Calcium	ppm	ASTM D5185m		1453	---	---
Phosphorus	ppm	ASTM D5185m		757	---	---
Zinc	ppm	ASTM D5185m		845	---	---
Sulfur	ppm	ASTM D5185m		31241	---	---
Acid Number (AN)	mg KOH/g	ASTM D8045		1.77	---	---
Base Number (BN)	mg KOH/g	ASTM D2896		10.10	---	---
Visc @ 40°C	cSt	ASTM D445		11.2	---	---
Visc @ 100°C	cSt	ASTM D445		3.28	---	---
Viscosity Index (VI)	Scale	ASTM D2270		177	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : HPL0004354
Lab Number : 06192657
Unique Number : 11049409
Test Package : MOB 2 (Additional Tests: FT-IR, ICP-NewOil, KV100, PrtCount, TBN, VI)

Received : 28 May 2024
Tested : 04 Jun 2024
Diagnosed : 04 Jun 2024 - Doug Bogart

HIGH PERFORMANCE LUBRICANTS LLC
 500 S SPRUCE ST
 MANTENO, IL
 US 60950
 Contact: DAVID WARD
 sampledata@hplubricants.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (815)468-3535

F: x: