

**WEAR** CONTAMINATION **FLUID CONDITION** 


**NORMAL NORMAL NORMAL** 

Machine Id

## 24E2104 JR1-200

New (Unused) Oil

RECOMMENDATION  This is a baseline read-out on the submitted sample.	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		HPL0004351		
	Sample Date		Client Info		22 May 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		0		
	Chromium	ppm	ASTM D5185m		0		
	Nickel		ASTM D5105m		<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		ν <1		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		ν <1		
	Vanadium	ppm	ASTM D5185m		<1 <1		
	White Metal	ppm	*Visual	NONE	NONE		
	Yellow Metal	scalar scalar		NONE	NONE		
	Tollow Motal	·····					
CONTAMINATION	Silicon	ppm	ASTM D5185m		10		
	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	<b>Emulsified Water</b>	scalar	*Visual		NEG		
FLUID CONDITION	Sodium	nnm	ASTM D5185m		2		
TEGID CONDITION	Boron	ppm	ASTM D5185m		7		
	Barium	ppm	ASTM D5185m				
	Molybdenum	ppm	ASTM D5185m		0 224		
			ASTM D5185m				
	Manganese Magnesium	ppm	ASTM D5185m		<1 12		
	-	ppm					
	Calcium	ppm	ASTM D5185m		1726		
	Phosphorus	ppm	ASTM D5185m		1868		
	Zinc	ppm	ASTM D5185m		2088		
	Sulfur	ppm	ASTM D5185m		15702		
	, ,	mg KOH/g	ASTM D8045		3.34		
	Visc @ 40°C	cSt	ASTM D445		59.05		
	Visc @ 100°C	cSt	ASTM D445		9.82		
	Viscosity Index (VI)		ASTM D2270		151		







Certificate L2367

Laboratory Sample No.

: HPL0004351 **Lab Number** : 06192670 Unique Number : 11049422

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received **Tested** 

Diagnosed Test Package : MOB 2 ( Additional Tests: FT-IR, ICP-NewOil, KV100, PrtCount, VI )

: 30 May 2024 : 30 May 2024 - Doug Bogart

: 28 May 2024

500 S SPRUCE ST MANTENO, IL US 60950 Contact: DAVID WARD

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

sampledata@hplubricants.com T: (815)468-3535

HIGH PERFORMANCE LUBRICANTS LLC

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: x: