


WEAR CONTAMINATION **FLUID CONDITION**

NORMAL NORMAL NORMAL

Machine Id

24E1604 AS-500 Component New (Unused) Oil

NOT GIVEN (GAL)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
This is a baseline read-out on the submitted sample.	Sample Number		Client Info		HPL0004366		
	Sample Date		Client Info		20 May 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		0		
	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		6		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		2		
	Potassium	ppm	ASTM D5185m	>20	1		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual		NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2		
	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		2		
	Molybdenum	ppm	ASTM D5185m		2		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		5		
	Calcium	ppm	ASTM D5185m		689		
	Phosphorus	ppm	ASTM D5185m		1786		
	Zinc	ppm	ASTM D5185m		22		
	Sulfur	ppm	ASTM D5185m		6759		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.44		
	Visc @ 40°C	cSt	ASTM D445		38.67		
			4 OT1 4 D 4 4 E		0.00		
	Visc @ 100°C	cSt	ASTM D445		6.63		







Certificate L2367

Laboratory Sample No.

Lab Number : 06192673

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : HPL0004366

Unique Number : 11049425

Received : 28 May 2024 **Tested** : 30 May 2024 Diagnosed

: 30 May 2024 - Doug Bogart Test Package : MOB 2 (Additional Tests: FT-IR, ICP-NewOil, KV100, PrtCount, VI)

HIGH PERFORMANCE LUBRICANTS LLC 500 S SPRUCE ST MANTENO, IL

> US 60950 Contact: DAVID WARD sampledata@hplubricants.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (815)468-3535 F: x:

Submitted By: DAVID WARD