



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
MACK PINNACLE 64T ZT2213 (S/N 1M1PN4GY4KM001196)
 Component
Diesel Engine
 Fluid
DURALENE Dura-Max Xtreme 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DC0035644	DC0028892	DC0027537
Sample Date		Client Info		21 May 2024	07 Nov 2023	23 May 2023
Machine Age	mls	Client Info		0	191333	174867
Oil Age	mls	Client Info		207109	16466	174867
Filter Age	mls	Client Info		0	16466	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	14	13	15
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>5	<1	0	<1
Titanium	ppm	ASTM D5185m	>2	<1	0	0
Silver	ppm	ASTM D5185m	>2	1	<1	0
Aluminum	ppm	ASTM D5185m	>20	3	4	3
Lead	ppm	ASTM D5185m	>40	3	4	3
Copper	ppm	ASTM D5185m	>330	4	2	4
Tin	ppm	ASTM D5185m	>15	1	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	7	6	7
Potassium	ppm	ASTM D5185m	>20	3	<1	2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>4	0.5	0.6	0.5
Nitration	Abs/cm	*ASTM D7624	>20	9.3	10.1	10.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.8	23.5	23.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	2	0
Boron	ppm	ASTM D5185m		4	20	27
Barium	ppm	ASTM D5185m		<1	0	2
Molybdenum	ppm	ASTM D5185m		54	47	58
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		767	541	508
Calcium	ppm	ASTM D5185m		1153	1576	1685
Phosphorus	ppm	ASTM D5185m		889	796	924
Zinc	ppm	ASTM D5185m		1099	1070	1131
Sulfur	ppm	ASTM D5185m		2857	2611	3335
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.4	21.9	21.5
Base Number (BN)	mg KOH/g	ASTM D2896		8.47	8.03	9.18
Visc @ 100°C	cSt	ASTM D445		14.17	13.1	12.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DC0035644
Lab Number : 06193056
Unique Number : 11049808
Test Package : MOB 2

Received : 28 May 2024
Tested : 31 May 2024
Diagnosed : 31 May 2024 - Sean Felton

COMER CONSTRUCTION
 2100 SLADE LANE
 FOREST HILL, MD
 US 21050
 Contact: DONALD FOX
 dfox@comerconstruction.com
 T: (443)269-1379
 F: (410)638-0289

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)