WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


[W22297 BURNETT]

JOHN DEERE 6120M 1L06120MCMG131093

Front Differential

fluid
{not provided} (--- GAL)

| {not provided} (GAL) | | | | | | | |
|---|------------------|--------|-------------|-----------|-------------|----------|----------|
| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
| Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample. | Sample Number | | Client Info | | JR0210814 | | |
| | Sample Date | | Client Info | | 22 May 2024 | | |
| | Machine Age | hrs | Client Info | | 482 | | |
| | Oil Age | hrs | Client Info | | 0 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Changed | | |
| | Filter Changed | | Client Info | | Changed | | |
| | Sample Status | | | | NORMAL | | |
| WEAR | PQ | | ASTM D8184 | | 247 | | |
| All component wear rates are normal. | Iron | ppm | ASTM D5185m | >500 | 311 | | |
| | Chromium | ppm | ASTM D5185m | | 4 | | |
| | Nickel | ppm | ASTM D5185m | >10 | 1 | | |
| | Titanium | ppm | ASTM D5185m | | <1 | | |
| | Silver | ppm | ASTM D5185m | | 1 | | |
| | Aluminum | ppm | ASTM D5185m | >25 | <1 | | |
| | Lead | ppm | ASTM D5185m | >25 | <1 | | |
| | Copper | ppm | ASTM D5185m | >100 | 2 | | |
| | Tin | ppm | ASTM D5185m | >10 | <1 | | |
| | Vanadium | ppm | ASTM D5185m | | <1 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| CONTAMINATION There is no indication of any contamination in the oil. | Silicon | ppm | ASTM D5185m | >75 | 51 | | |
| | Potassium | ppm | ASTM D5185m | >20 | 2 | | |
| | Water | | WC Method | >.2 | NEG | | |
| | Silt | scalar | *Visual | NONE | MODER | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >.2 | NEG | | |
| FLUID CONDITION | Sodium | ppm | ASTM D5185m | | 3 | | |
| The condition of the oil is acceptable for the time in service. | Boron | ppm | ASTM D5185m | | 120 | | |
| | Barium | ppm | ASTM D5185m | | 2 | | |
| | Molybdenum | ppm | ASTM D5185m | | <1 | | |
| | Manganese | ppm | ASTM D5185m | | 15 | | |
| | Magnesium | ppm | ASTM D5185m | | 5 | | |
| | Calcium | ppm | ASTM D5185m | | 798 | | |
| | Phosphorus | ppm | ASTM D5185m | | 645 | | |
| | Zinc | ppm | ASTM D5185m | | 1332 | | |
| | Sulfur | ppm | ASTM D5185m | | 5498 | | |
| | Visc @ 40°C | cSt | ASTM D445 | | 79.6 | | |





Laboratory Sample No.

Lab Number : 06193067 Unique Number : 11049819

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0210814

Received : 28 May 2024 **Tested** Diagnosed

: 30 May 2024 : 30 May 2024 - Wes Davis

JRE - BURKEVILLE 510 WEST COLONIAL DR BURKEVILLE, VA

US 23922 Contact: BRANDON BOLLING bbolling@jamesriverequipment.com

Test Package : CONST (Additional Tests: PQ) To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

T: (434)767-5578 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (434)767-3774