**WEAR** CONTAMINATION **FLUID CONDITION** 


**NORMAL NORMAL NORMAL** 


Machine Id


**CR4416** Component


2 Winch
Fluid

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		WC0935946	WC0555993	
	Sample Date		Client Info		10 May 2024	22 Sep 2022	
	Machine Age	hrs	Client Info		9594	6260	
	Oil Age	hrs	Client Info		3334	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		Not Changd	N/A	
	Sample Status				NORMAL	ABNORMAL	
VEAR	Iron	ppm	ASTM D5185m	>150	60	68	
	Chromium	ppm	ASTM D5185m		1	<1	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		<1	0	
	Titanium	ppm	ASTM D5185m	,	<1	<1	
	Silver	ppm	ASTM D5185m		1	0	
	Aluminum	ppm	ASTM D5185m	>5	<1	<1	
	Lead	ppm	ASTM D5185m		<1	0	
	Copper	ppm	ASTM D5185m	>80	1	<1	
	Tin	ppm	ASTM D5185m		<1	0	
	Vanadium	ppm	ASTM D5185m		<1	<1	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	nnm	ASTM D5185m	> 25	4	3	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		2	0	
	Water	ppiii	WC Method		NEG	NEG	
	Silt	scalar	*Visual	NONE	MODER	NONE	
	Debris	scalar	*Visual	NONE	NONE	▲ MODER	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
LUID CONDITION	Sodium	ppm	ASTM D5185m		1	0	
	Boron	ppm	ASTM D5185m	50	11	3	
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		<1	<1	
	Manganese	ppm	ASTM D5185m		1	2	
	Magnesium	ppm	ASTM D5185m	50	<1	- <1	
	Calcium	ppm	ASTM D5185m		19	8	
	Phosphorus	ppm	ASTM D5185m		368	372	
	Zinc	ppm	ASTM D5185m		31	4	
	Sulfur	ppm	ASTM D5185m	12500	6001	13710	
	Visc @ 40°C	cSt	ASTM D445		226	245	











Certificate L2367

Laboratory Sample No.

: WC0935946 Lab Number : 06193106 Unique Number : 11049858 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 28 May 2024 **Tested** : 30 May 2024 Diagnosed

: 30 May 2024 - Wes Davis

GRAHAM, NC US 27253-9215

**BUCKNER HEAVY LIFT** 

4732 NC 54 EAST

Contact: MICHAEL LAWSON michaell@bucknercompanies.com

T: (336)376-8888 F: (336)376-4090

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)