

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL

[PAC7025] PETERBILT 496-479

Diesel Engine


CITGO CITGUARD 600 15W40 (48 QTS)

					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		RPL0004352		
	Sample Date		Client Info		14 May 2024		
	Machine Age	mls	Client Info		260784		
	Oil Age	mls	Client Info		13585		
	Filter Age	mls	Client Info		13585		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		13		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		1		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m	>5	0		
	Vanadium	ppm	ASTM D5185m	NONE	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>35	4		
	Potassium	ppm	ASTM D5185m		3		
There is no indication of any contamination in the oil.	Fuel	1-1-	WC Method		<1.0		
	Water		WC Method		NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>7.5	0.2		
	Nitration	Abs/cm	*ASTM D7624	>20	8.2		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	20.9		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	0				•		
	Sodium	ppm	ASTM D5185m	10	0		
	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	57	64		
	Manganese	ppm	ASTM D5185m	005	<1		
	Magnesium	ppm	ASTM D5185m		488		
	Calcium	ppm	ASTM D5185m		2123		
	Phosphorus	ppm	ASTM D5185m		1252		
	Zinc	ppm	ASTM D5185m		1557		
	Sulfur	ppm	ASTM D5185m		4551		
	Oxidation	Abs/.1mm	*ASTM D7414		17.0		
	Base Number (BN)	mg KOH/g	ASTM D2896	11.0	8.1		

Visc @ 100°C cSt

ASTM D445 15.4

13.1



RTL PACLEASE - 7025 - Tampa Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Received 8109 East Adamo Drive : RPL0004352 : 28 May 2024 Lab Number : 06193314 Tested : 30 May 2024 Tampa, FL Unique Number : 11050066 Diagnosed : 30 May 2024 - Wes Davis US 33619 Test Package : FLEET Contact: Michael Reid Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. REIDM@RushEnterprises.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (813)371-2130 F:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: TECHNICIAN ACCOUNT Page 2 of 2