



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
526011
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0110197	GFL0110182	GFL0060422
Sample Date		Client Info		24 May 2024	01 Feb 2024	06 Jan 2023
Machine Age	hrs	Client Info		7767	7525	6600
Oil Age	hrs	Client Info		242	600	600
Filter Age	hrs	Client Info		242	600	600
Oil Changed		Client Info		Not Chngd	Changed	Changed
Filter Changed		Client Info		Not Chngd	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	5	9	8
Chromium	ppm	ASTM D5185m	>20	0	<1	0
Nickel	ppm	ASTM D5185m	>5	0	<1	0
Titanium	ppm	ASTM D5185m	>2	0	<1	0
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	2	5	<1
Lead	ppm	ASTM D5185m	>40	<1	1	<1
Copper	ppm	ASTM D5185m	>330	<1	4	2
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	4	3	2
Potassium	ppm	ASTM D5185m	>20	2	6	3
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>4	0.2	0.5	0.4
Nitration	Abs/cm	*ASTM D7624	>20	6.7	9.1	8.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.8	20.4	18.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	2	0
Boron	ppm	ASTM D5185m	0	4	4	0
Barium	ppm	ASTM D5185m	0	0	<1	2
Molybdenum	ppm	ASTM D5185m	60	57	58	54
Manganese	ppm	ASTM D5185m	0	<1	0	0
Magnesium	ppm	ASTM D5185m	1010	968	824	801
Calcium	ppm	ASTM D5185m	1070	1189	1023	1085
Phosphorus	ppm	ASTM D5185m	1150	1087	935	949
Zinc	ppm	ASTM D5185m	1270	1397	1148	1135
Sulfur	ppm	ASTM D5185m	2060	4016	2811	2613
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.4	15.4	14.2
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.7	5.7	7.6
Visc @ 100°C	cSt	ASTM D445	15.4	13.1	12.9	13.0



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0110197 **Received** : 28 May 2024
Lab Number : 06193334 **Tested** : 30 May 2024
Unique Number : 11050086 **Diagnosed** : 30 May 2024 - Wes Davis
Test Package : FLEET

GFL Environmental - 660 - Lynchburg Hauling
 2410 Mayflower Drive
 Lynchburg, VA
 US 24501
 Contact: Delbert Beasley
 dbeasley@countryrecycling.net
 T: (434)665-5998
 F:

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)