



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
933040
Component
Natural Gas Engine
Fluid
PETRO CANADA DURON SHP 15W40 (21 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0122642	GFL0103429	GFL0074629
Sample Date		Client Info		27 May 2024	12 Mar 2024	30 Nov 2023
Machine Age	hrs	Client Info		2224	1764	1201
Oil Age	hrs	Client Info		1023	563	1201
Filter Age	hrs	Client Info		1023	554	1201
Oil Changed		Client Info		Changed	Not Changd	Changed
Filter Changed		Client Info		Changed	Not Changd	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	40	40	▲ 106
Chromium	ppm	ASTM D5185m	>5	3	2	3
Nickel	ppm	ASTM D5185m	>4	2	<1	3
Titanium	ppm	ASTM D5185m	>5	0	0	<1
Silver	ppm	ASTM D5185m	>3	<1	0	<1
Aluminum	ppm	ASTM D5185m	>25	13	7	23
Lead	ppm	ASTM D5185m	>40	2	<1	2
Copper	ppm	ASTM D5185m	>150	4	3	17
Tin	ppm	ASTM D5185m	>4	2	0	2
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	10	8	22
Potassium	ppm	ASTM D5185m	>20	26	10	68
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	10.2	10.4	12.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.4	21.5	24.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		9	6	5
Boron	ppm	ASTM D5185m	0	6	<1	3
Barium	ppm	ASTM D5185m	0	0	0	4
Molybdenum	ppm	ASTM D5185m	60	80	71	65
Manganese	ppm	ASTM D5185m	0	3	2	15
Magnesium	ppm	ASTM D5185m	1010	1039	965	820
Calcium	ppm	ASTM D5185m	1070	1290	1262	1132
Phosphorus	ppm	ASTM D5185m	1150	1127	973	791
Zinc	ppm	ASTM D5185m	1270	1397	1307	1037
Sulfur	ppm	ASTM D5185m	2060	3097	3239	3320
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.5	16.0	22.2
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	4.4	3.9	3.8
Visc @ 100°C	cSt	ASTM D445	15.4	13.0	13.2	13.6



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0122642
Lab Number : 06193406
Unique Number : 11050158
Test Package : FLEET

Received : 28 May 2024
Tested : 30 May 2024
Diagnosed : 30 May 2024 - Wes Davis

GFL Environmental - 095 - Atlanta West
 2699 Cochran Industrial Blvd
 Douglasville, GA
 US 30127-1332

Contact: Darrell Welch
 darrell.welch@gflenv.com

T: (800)207-6618
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)