



# OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area  
**Store 9 - Marietta**

Machine Id  
**1099**

Component  
**Diesel Engine**

Fluid  
**SHELL ROTELLA T 15W40 (--- GAL)**

## RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>LEC0050622</b>	LEC0048066	LEC0047095
Sample Date		Client Info		<b>11 May 2024</b>	15 Feb 2024	30 Jan 2024
Machine Age	mls	Client Info		<b>37675</b>	526442	366051
Oil Age	mls	Client Info		<b>5000</b>	5000	5000
Filter Age	mls	Client Info		<b>5000</b>	5000	5000
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	MARGINAL

## WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	<b>20</b>	6	7
Chromium	ppm	ASTM D5185m	>20	<b>1</b>	<1	<1
Nickel	ppm	ASTM D5185m	>4	<b>&lt;1</b>	0	0
Titanium	ppm	ASTM D5185m		<b>4</b>	0	0
Silver	ppm	ASTM D5185m	>3	<b>1</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>4</b>	3	4
Lead	ppm	ASTM D5185m	>40	<b>3</b>	<1	<1
Copper	ppm	ASTM D5185m	>330	<b>1</b>	<1	0
Tin	ppm	ASTM D5185m	>15	<b>1</b>	<1	<1
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

## CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>120	<b>7</b>	6	4
Potassium	ppm	ASTM D5185m	>20	<b>27</b>	2	11
Fuel		WC Method	>5	<b>&lt;1.0</b>	<1.0	▲ 2.2
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>3	<b>0.6</b>	0.3	0.3
Nitration	Abs/cm	*ASTM D7624	>20	<b>11.0</b>	8.4	8.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>24.5</b>	23.9	24.0
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

## FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>8</b>	2	3
Boron	ppm	ASTM D5185m	316	<b>210</b>	275	313
Barium	ppm	ASTM D5185m	0.0	<b>0</b>	0	<1
Molybdenum	ppm	ASTM D5185m	1.2	<b>112</b>	135	132
Manganese	ppm	ASTM D5185m		<b>1</b>	<1	<1
Magnesium	ppm	ASTM D5185m	24	<b>666</b>	710	661
Calcium	ppm	ASTM D5185m	2292	<b>1521</b>	1590	1460
Phosphorus	ppm	ASTM D5185m	1064	<b>709</b>	765	722
Zinc	ppm	ASTM D5185m	1160	<b>836</b>	942	842
Sulfur	ppm	ASTM D5185m	4996	<b>2932</b>	2614	2353
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>19.6</b>	17.9	18.4
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	<b>7.4</b>	8.2	8.5
Visc @ 100°C	cSt	ASTM D445	15.7	<b>12.6</b>	13.3	12.8



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : LEC0050622 **Received** : 29 May 2024  
**Lab Number** : 06193632 **Tested** : 30 May 2024  
**Unique Number** : 11050384 **Diagnosed** : 30 May 2024 - Sean Felton  
**Test Package** : CONST ( Additional Tests: TBN )

**HALL DRILLING LLC**  
 PO BOX 249  
 ELLENBORO, WV  
 US 26346

Contact: CHRIS PETROVICH  
 chrispetrovich@halldrilling.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (304)869-3404  
 F: (304)869-3408