



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
722021-310026
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0120142	GFL0117161	GFL0114048
Sample Date		Client Info		24 May 2024	23 Apr 2024	22 Mar 2024
Machine Age	hrs	Client Info		20649	20507	22801
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>110	35	22	<1
Chromium	ppm	ASTM D5185m	>4	4	2	0
Nickel	ppm	ASTM D5185m	>2	1	1	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>2	1	<1	0
Aluminum	ppm	ASTM D5185m	>25	6	3	<1
Lead	ppm	ASTM D5185m	>45	1	2	0
Copper	ppm	ASTM D5185m	>85	2	4	<1
Tin	ppm	ASTM D5185m	>4	1	1	0
Vanadium	ppm	ASTM D5185m		<1	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>30	17	8	2
Potassium	ppm	ASTM D5185m	>20	9	4	2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.5	0.9	0.1
Nitration	Abs/cm	*ASTM D7624	>20	8.7	10.2	4.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.2	20.8	17.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		5	5	2
Boron	ppm	ASTM D5185m	0	3	4	13
Barium	ppm	ASTM D5185m	0	0	<1	0
Molybdenum	ppm	ASTM D5185m	60	57	60	56
Manganese	ppm	ASTM D5185m	0	1	1	0
Magnesium	ppm	ASTM D5185m	1010	850	867	943
Calcium	ppm	ASTM D5185m	1070	1078	1072	1138
Phosphorus	ppm	ASTM D5185m	1150	938	926	937
Zinc	ppm	ASTM D5185m	1270	1119	1154	1301
Sulfur	ppm	ASTM D5185m	2060	3108	3057	3781
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.0	17.9	13.7
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.3	8.1	8.9
Visc @ 100°C	cSt	ASTM D445	15.4	12.5	13.3	14.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0120142
Lab Number : 06193662
Unique Number : 11050414
Test Package : FLEET

Received : 29 May 2024
Tested : 30 May 2024
Diagnosed : 30 May 2024 - Sean Felton

GFL Environmental - 836 - Kansas City Hauling
 7801 East Truman Road
 Kansas City, MO
 US 64126
 Contact: Loyce Stewart
 loyce.stewart@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: