

## WEAR NORMAL CONTAMINATION ABNORMAL FLUID CONDITION NORMAL

Machine Id VOLVO A40G 352122 Component Hydraulic System Fluid {not provided} (--- GAL)

RECOMMENDATION

The filter change at the time of sampling has been noted. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

**WEAR** 

All component wear rates are normal.

\_\_\_\_\_

## CONTAMINATION


There is a moderate amount of visible silt present in the sample.


					_
		$\mathbf{co}$		TION	
FLU	U.	COI	ועא	TION	

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP423889		
Sample Date		Client Info		02 May 2024		
Machine Age	hrs	Client Info		1249		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Filter Changed		Client Info		Changed		
Sample Status				ABNORMAL		
				_		
Iron	ppm	ASTM D5185m	>50	5		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>20	<1		
Lead	ppm	ASTM D5185m	>20	2		
Copper	ppm	ASTM D5185m	>150	3		
Tin	ppm	ASTM D5185m	>20	<1		
Vanadium	ppm	ASTM D5185m		<1		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>20	4		
Potassium	ppm	ASTM D5185m	>20	2		
Water	ppin	WC Method	>0.1	2 NEG		
Silt	scalar	*Visual	NONE			
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
	Scalai	visuai	>0.1	NEG		
Sodium	ppm	ASTM D5185m		2		
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		1		
Calcium	ppm	ASTM D5185m		54		
Phosphorus	ppm	ASTM D5185m		359		
Zinc	ppm	ASTM D5185m		449		
Sulfur	ppm	ASTM D5185m		1834		
Acid Number (AN)	mg KOH/g	ASTM D8045		0.37		
Visc @ 40°C	cSt	ASTM D445		40.9		

Contact/Location: ALLEN WILLIAMS - VOLVO8769





Contact/Location: ALLEN WILLIAMS - VOLVO8769 Page 2 of 2