WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

## MATTEI 093556 - GAYLON'S BLADE

Compressor

ROTOROII 8000 (1 GAL)

ROTOROIL 8000 (1 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		AN38939	AN23672	
	Sample Date		Client Info		28 Jul 2023	25 Feb 2022	
	Machine Age	hrs	Client Info		4652	3160	
	Oil Age	hrs	Client Info		0	0	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				NORMAL	ABNORMAL	
WEAR	Iron	ppm	ASTM D5185m	\50	7	3	
WEAR	Chromium		ASTM D5185m		, <1	0	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m	>10		0	
		ppm			<1	-	
	Titanium	ppm	ASTM D5185m		<1	0	
	Silver	ppm	ASTM D5185m	, OF	1	0	
	Aluminum	ppm	ASTM D5185m		8	11	
	Lead	ppm	ASTM D5185m		<1	<1	
	Copper	ppm	ASTM D5185m		2	1	
	Tin	ppm	ASTM D5185m	>15	<1	0	
	Vanadium	ppm	ASTM D5185m		<1	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	13	<b>△</b> 30	
The water content is negligible. There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2	0	
	Water	%	ASTM D6304	>0.1	0.025	0.023	
	ppm Water	ppm	ASTM D6304	>1000	253	238.6	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	VLITE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	<b>Emulsified Water</b>	scalar	*Visual	>0.1	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		5	2	
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		0	0	
	Barium	ppm	ASTM D5185m		0	0	
	Molybdenum	ppm	ASTM D5185m		<1	0	
	Manganese	ppm	ASTM D5185m		<1	<1	
	Magnesium	ppm	ASTM D5185m		<1	0	
	Calcium	ppm	ASTM D5185m		0	0	
	Phosphorus	ppm	ASTM D5185m	884	887	827	
	Zinc	ppm	ASTM D5185m	00-T	32	21	
	Sulfur		ASTM D5185m		92	227	
		ppm mg KOU/g		0.1			
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.41	0.52	
Report Id: MATTEL[WLISCAR] 06194058 (Generated: 05/31/2024 19:39:20) Rev: 1	Visc @ 40°C	cSt	ASTM D445		90.4	90.9	







Certificate L2367

Laboratory Sample No.

: AN38939 Lab Number : 06194058 Unique Number : 11056181 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 29 May 2024 **Tested** : 31 May 2024

Diagnosed : 31 May 2024 - Jonathan Hester

US 21133 Contact: MARTY WARD jward@matteicomp.com

MATTEI COMPRESSORS--OEM

9635 LIBERTY ROAD, SUITE E

T: (410)521-7020 F: (410)521-7024

RANDALLSTOWN, MD

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)