



| | |
|-----------------|---------------|
| WEAR | NORMAL |
| CONTAMINATION | NORMAL |
| FLUID CONDITION | NORMAL |

Machine Id
C333419 (S/N 21200552)
Component
Rear Right Final Drive
Fluid
COMP OIL (POE) ISO 220 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

| Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|----------------|-----|-------------|-----------|--------------------|----------|----------|
| Sample Number | | Client Info | | JR0215873 | --- | --- |
| Sample Date | | Client Info | | 24 May 2024 | --- | --- |
| Machine Age | hrs | Client Info | | 333 | --- | --- |
| Oil Age | hrs | Client Info | | 300 | --- | --- |
| Filter Age | hrs | Client Info | | 0 | --- | --- |
| Oil Changed | | Client Info | | Changed | --- | --- |
| Filter Changed | | Client Info | | N/A | --- | --- |
| Sample Status | | | | NORMAL | --- | --- |

WEAR

All component wear rates are normal.

| | | | | | | |
|--------------|--------|-------------|------|--------------|-----|-----|
| PQ | | ASTM D8184 | | 337 | --- | --- |
| Iron | ppm | ASTM D5185m | >500 | 22 | --- | --- |
| Chromium | ppm | ASTM D5185m | >10 | 0 | --- | --- |
| Nickel | ppm | ASTM D5185m | >10 | <1 | --- | --- |
| Titanium | ppm | ASTM D5185m | | 0 | --- | --- |
| Silver | ppm | ASTM D5185m | | 0 | --- | --- |
| Aluminum | ppm | ASTM D5185m | >25 | 1 | --- | --- |
| Lead | ppm | ASTM D5185m | >25 | 0 | --- | --- |
| Copper | ppm | ASTM D5185m | >50 | <1 | --- | --- |
| Tin | ppm | ASTM D5185m | >10 | 0 | --- | --- |
| Vanadium | ppm | ASTM D5185m | | 0 | --- | --- |
| White Metal | scalar | *Visual | NONE | HEAVY | --- | --- |
| Yellow Metal | scalar | *Visual | NONE | NONE | --- | --- |

CONTAMINATION







There is no indication of any contamination in the fluid.

| | | | | | | |
|------------------|--------|-------------|-------|--------------|-----|-----|
| Silicon | ppm | ASTM D5185m | >75 | 11 | --- | --- |
| Potassium | ppm | ASTM D5185m | >20 | 4 | --- | --- |
| Water | | WC Method | >0.2 | NEG | --- | --- |
| Silt | scalar | *Visual | NONE | NONE | --- | --- |
| Debris | scalar | *Visual | NONE | NONE | --- | --- |
| Sand/Dirt | scalar | *Visual | NONE | NONE | --- | --- |
| Appearance | scalar | *Visual | NORML | NORML | --- | --- |
| Odor | scalar | *Visual | NORML | NORML | --- | --- |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | --- | --- |

FLUID CONDITION

The condition of the fluid is suitable for further service.

| | | | | | | |
|-------------|-----|-------------|-----|--------------|-----|-----|
| Sodium | ppm | ASTM D5185m | | 2 | --- | --- |
| Boron | ppm | ASTM D5185m | 5 | 0 | --- | --- |
| Barium | ppm | ASTM D5185m | 5 | 0 | --- | --- |
| Molybdenum | ppm | ASTM D5185m | 5 | 0 | --- | --- |
| Manganese | ppm | ASTM D5185m | | <1 | --- | --- |
| Magnesium | ppm | ASTM D5185m | 5 | 4 | --- | --- |
| Calcium | ppm | ASTM D5185m | 5 | 8 | --- | --- |
| Phosphorus | ppm | ASTM D5185m | 400 | 333 | --- | --- |
| Zinc | ppm | ASTM D5185m | 5 | 0 | --- | --- |
| Sulfur | ppm | ASTM D5185m | 100 | 412 | --- | --- |
| Visc @ 40°C | cSt | ASTM D445 | 220 | 226 | --- | --- |



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : JR0215873

Lab Number : 06194261

Unique Number : 11056384

Test Package : CONST (Additional Tests: PQ)

Received : 29 May 2024

Tested : 31 May 2024

Diagnosed : 31 May 2024 - Sean Felton

JRE - CHARLOTTE

9550 STATESVILLE ROAD

CHARLOTTE, NC

US 28269

Contact: CHARLOTTE SHOP

myoung@jamesriverequipment.com

T: (704)597-0211

F: (704)596-6198

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)