



VOLVO

OIL ANALYSIS REPORT

| | |
|-----------------|---------------|
| WEAR | NORMAL |
| CONTAMINATION | NORMAL |
| FLUID CONDITION | NORMAL |



Machine Id
VOLVO A30G 742023
Component
Rear Axle
Fluid
VOLVO PREMIUM GEAR OIL 85W-140 GL-5 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

| Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|----------------|-----|-------------|-----------|--------------------|-------------|-------------|
| Sample Number | | Client Info | | VCP440137 | VCP436062 | VCP393399 |
| Sample Date | | Client Info | | 02 Apr 2024 | 11 Sep 2023 | 08 Mar 2023 |
| Machine Age | hrs | Client Info | | 9289 | 8246 | 7220 |
| Oil Age | hrs | Client Info | | 0 | 4000 | 1500 |
| Filter Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | Changed | Not Changd |
| Filter Changed | | Client Info | | Not Changed | Changed | Not Changed |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |

WEAR

All component wear rates are normal.

| | | | | | | |
|--------------|--------|-------------|------|-------------|------|------|
| Iron | ppm | ASTM D5185m | >900 | 59 | 127 | 37 |
| Chromium | ppm | ASTM D5185m | >20 | 0 | 2 | <1 |
| Nickel | ppm | ASTM D5185m | >10 | 0 | 1 | 0 |
| Titanium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >30 | 0 | 0 | 1 |
| Lead | ppm | ASTM D5185m | >50 | 0 | <1 | 0 |
| Copper | ppm | ASTM D5185m | >150 | 4 | 6 | 4 |
| Tin | ppm | ASTM D5185m | >20 | 0 | <1 | 0 |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |

CONTAMINATION










There is no indication of any contamination in the oil.

| | | | | | | |
|------------------|--------|-------------|-------|--------------|-------|-------|
| Silicon | ppm | ASTM D5185m | >50 | 5 | 4 | 5 |
| Potassium | ppm | ASTM D5185m | >20 | 0 | <1 | 0 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| Silt | scalar | *Visual | NONE | NONE | NONE | MODER |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

| | | | | | | |
|-------------|-----|-------------|-------|--------------|-------|-------|
| Sodium | ppm | ASTM D5185m | | 0 | 0 | 1 |
| Boron | ppm | ASTM D5185m | 111 | 173 | 187 | 143 |
| Barium | ppm | ASTM D5185m | 0.0 | 0 | 1 | 0 |
| Molybdenum | ppm | ASTM D5185m | 0.9 | 3 | 2 | 1 |
| Manganese | ppm | ASTM D5185m | 0.0 | <1 | 2 | <1 |
| Magnesium | ppm | ASTM D5185m | 39 | 41 | 5 | 4 |
| Calcium | ppm | ASTM D5185m | 93 | 205 | 93 | 471 |
| Phosphorus | ppm | ASTM D5185m | 920 | 1251 | 1424 | 1279 |
| Zinc | ppm | ASTM D5185m | 104 | 136 | 47 | 249 |
| Sulfur | ppm | ASTM D5185m | 20179 | 29369 | 30035 | 25672 |
| Visc @ 40°C | cSt | ASTM D445 | 333 | 244 | 142 | 111 |



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VCP440137
Lab Number : 06194376
Unique Number : 11056499
Test Package : MOB 1

Received : 29 May 2024
Tested : 31 May 2024
Diagnosed : 31 May 2024 - Wes Davis

RIPA AND ASSOCIATES
 10149 FISHER AVENUE
 TAMPA, FL
 US 33619

Contact: PM Services
 PMServices@ripaconstruction.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: