

[ATF] Machine Id VOLVO L110H 631951 Component Transmission (Auto)

VOLVO AUTOMATIC TRANSMISSION FLUID AT102 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP454948		
	Sample Date		Client Info		21 May 2024		
	Machine Age	hrs	Client Info		3512		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>160	72		
	Chromium	ppm	ASTM D5185m		<1		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	>5	<1		
	Aluminum	ppm	ASTM D5185m	>50	6		
	Lead	ppm	ASTM D5185m	>50	<1		
	Copper	ppm	ASTM D5185m	>225	7		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	10		
There is no indication of any contamination in the fluid.	Potassium	ppm	ASTM D5185m		2		
	Water	1-1-	WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		7		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185m	187	46		
	Barium	ppm	ASTM D5185m		6		
	Molybdenum	ppm	ASTM D5185m	0.0	<1		
	Manganese	ppm	ASTM D5185m	0.0	6		
	Magnesium	ppm	ASTM D5185m	6.8	<1		
	Calcium	ppm	ASTM D5185m	215	74		
	Phosphorus	ppm	ASTM D5185m	445	140		
	Zinc	ppm	ASTM D5185m	56	28		
	Sulfur	ppm	ASTM D5185m	1336	1794		


Visc @ 40°C


cSt


Contact/Location: KENNY HANEY - VOLVO0093

26.0

ASTM D445 35.3







Contact/Location: KENNY HANEY - VOLVO0093 Page 2 of 2