



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
(26812XA)
Machine Id
527018-7011
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- LTR)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0070923	GFL0070966	GFL0058113
Sample Date		Client Info		28 May 2024	11 Mar 2024	20 Feb 2024
Machine Age	hrs	Client Info		18485	18367	18178
Oil Age	hrs	Client Info		776	0	409
Filter Age	hrs	Client Info		776	0	409
Oil Changed		Client Info		Changed	Not Changd	N/A
Filter Changed		Client Info		Changed	Not Changd	N/A
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	24	36	31
Chromium	ppm	ASTM D5185m	>20	<1	1	<1
Nickel	ppm	ASTM D5185m	>5	4	5	4
Titanium	ppm	ASTM D5185m	>2	<1	0	0
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>20	12	▲ 32	26
Lead	ppm	ASTM D5185m	>40	1	0	0
Copper	ppm	ASTM D5185m	>330	2	3	3
Tin	ppm	ASTM D5185m	>15	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	12	11	10
Potassium	ppm	ASTM D5185m	>20	6	2	6
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>4	0.5	1.3	1
Nitration	Abs/cm	*ASTM D7624	>20	6.5	10.3	9.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.1	22.2	20.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		6	8	2
Boron	ppm	ASTM D5185m	0	1	<1	<1
Barium	ppm	ASTM D5185m	0	0	0	<1
Molybdenum	ppm	ASTM D5185m	60	57	59	69
Manganese	ppm	ASTM D5185m	0	<1	<1	0
Magnesium	ppm	ASTM D5185m	1010	866	966	1041
Calcium	ppm	ASTM D5185m	1070	1123	1091	1054
Phosphorus	ppm	ASTM D5185m	1150	1022	1007	933
Zinc	ppm	ASTM D5185m	1270	1148	1201	1338
Sulfur	ppm	ASTM D5185m	2060	3447	3057	2920
Oxidation	Abs/.1mm	*ASTM D7414	>25	13.8	17.6	16.2
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.2	6.3	7.3
Visc @ 100°C	cSt	ASTM D445	15.4	14.3	13.6	13.8



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0070923
Lab Number : 06194784
Unique Number : 11056907
Test Package : FLEET
Received : 29 May 2024
Tested : 30 May 2024
Diagnosed : 30 May 2024 - Wes Davis

GFL Environmental - 657 - Charlottesville Hauling
 5498 Richmond Road
 Troy, VA
 US 22974
 Contact: TECHNICIAN ACCOUNT
 catherine.anastasio@wearcheck.com
 T:
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)