



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
DMA
Machine Id
Component
DMA
Starboard Main Engine
Fluid
CHEVRON DELO 710 LS (300 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0050789	MW0065608	MW0031598
Sample Date		Client Info		22 May 2024	07 Apr 2024	18 Jun 2022
Machine Age	hrs	Client Info		3301	2246	27664
Oil Age	hrs	Client Info		1068	2246	13004
Filter Age	hrs	Client Info		1068	1224	1208
Oil Changed		Client Info		Not Chngd	Not Chngd	Not Chngd
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	42	49	20
Chromium	ppm	ASTM D5185m	>8	1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	0	1
Titanium	ppm	ASTM D5185m	>3	<1	<1	<1
Silver	ppm	ASTM D5185m	>2	<1	0	<1
Aluminum	ppm	ASTM D5185m	>15	3	2	2
Lead	ppm	ASTM D5185m	>18	16	10	9
Copper	ppm	ASTM D5185m	>80	24	27	30
Tin	ppm	ASTM D5185m	>14	9	9	6
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	6	6	18
Potassium	ppm	ASTM D5185m	>20	1	0	1
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	0.3	0.8
Nitration	Abs/cm	*ASTM D7624	>20	9.2	8.6	12.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.4	16.9	21.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	3	4	59
Boron	ppm	ASTM D5185m		33	40	46
Barium	ppm	ASTM D5185m		0	2	0
Molybdenum	ppm	ASTM D5185m		45	47	50
Manganese	ppm	ASTM D5185m		<1	2	<1
Magnesium	ppm	ASTM D5185m		34	13	22
Calcium	ppm	ASTM D5185m		3339	3458	3641
Phosphorus	ppm	ASTM D5185m		22	2	5
Zinc	ppm	ASTM D5185m		26	3	2
Sulfur	ppm	ASTM D5185m		2331	2367	2090
Oxidation	Abs/.1mm	*ASTM D7414	>25	11.1	10.3	14.7
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	5.6	6.0	7.6
Visc @ 100°C	cSt	ASTM D445	15.5	14.7	14.4	14.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0050789
Lab Number : 06194785
Unique Number : 11056908
Test Package : MAR 2

Received : 29 May 2024
Tested : 30 May 2024
Diagnosed : 30 May 2024 - Wes Davis

AMERICAN RIVER TRANSPORTATION CO.
P.O. BOX 2889
ST. LOUIS, MO
US 63111

Contact: BRIAN GRIEWING
brian.griewing@adm.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: (314)481-5278