WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

[W67134]

JOHN DEERE 135G 1FF135GXVKF501242

Swing Drive Gear Case

Inot provided (--- GAL)

{not provided} (GAL)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. (Customer Sample Comment: W67134)	Sample Number		Client Info		JR0215618		
	Sample Date		Client Info		28 May 2024		
	Machine Age	hrs	Client Info		5616		
	Oil Age	hrs	Client Info		1724		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
NEAD							
WEAR	PQ		ASTM D8184		16		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		0		
	Chromium	ppm	ASTM D5185m	>10	0		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		0		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ASTM D5185m		2		
CONTAMINATION	Potassium	ppm	ASTM D5185m	- 20	0		
There is no indication of any contamination in the oil.		ppm					
	Water Silt		WC Method	>0.2	NEG NONE		
		scalar	*Visual	NONE			
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		4		
	Calcium	ppm	ASTM D5185m		14		
	Phosphorus	ppm	ASTM D5185m		282		
	Zinc	ppm	ASTM D5185m		3		
	Sulfur	ppm	ASTM D5185m		19829		
	Visc @ 40°C	cSt	ASTM D445		141		
Report Id: JAMCHA [WUSCAR] 06195678 (Generated: 06/04/2024 06:27:19) Rev: 1	¥150 @ +0 O		t/Location: M	!!! V			





Certificate L2367

Laboratory

Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0215618 Lab Number : 06195678

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received **Tested** Unique Number : 11057801

: 03 Jun 2024 - Don Baldridge Diagnosed Test Package : CONST (Additional Tests: FT-IR, KV100, PQ)

9550 STATESVILLE ROAD : 30 May 2024 : 03 Jun 2024 CHARLOTTE, NC

US 28269 Contact: CHARLOTTE SHOP myoung@jamesriverequipment.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) T: (704)597-0211 F: (704)596-6198

JRE - CHARLOTTE