




## VOLVO L350H 1302 (S/N 1218)


**Rear Differential** 

VOLVO SUPER WET BRAKE TRANSAXLE OIL WB102 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		ASC0004816		
	Sample Date		Client Info		16 May 2024		
	Machine Age	hrs	Client Info		541		
	Oil Age	hrs	Client Info		541		
	Filter Age	hrs	Client Info		541		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAD							
WEAR	Iron	ppm	ASTM D5185m		116		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		3		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	10		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>.2	NEG		
	Silt	scalar	*Visual	NONE	LIGHT		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		113		
	Barium	ppm	ASTM D5185m		4		
	Molybdenum	ppm	ASTM D5185m		2		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m		8		
	Calcium	ppm	ASTM D5185m		3569		
	Phosphorus	ppm	ASTM D5185m		1210		
	Zinc	ppm	ASTM D5185m		1450		
	Sulfur	ppm	ASTM D5185m		11204		
	Visc @ 40°C	cSt	ASTM D445	55	54.5		

Submitted By: AMANDA KARI





∎₿

Lab Number : 06195744 Tested : 31 May 2024 QUITMAN, GA Unique Number : 11057867 Diagnosed : 31 May 2024 - Wes Davis US 31643 Test Package : CONST Contact: SERVICE MANAGER Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (229)263-8943 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Received

: 30 May 2024

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Report Id: LANQUI [WUSCAR] 06195744 (Generated: 05/31/2024 14:38:45) Rev: 1

Laboratory

Sample No.

: ASC0004816

Submitted By: AMANDA KARI Page 2 of 2

LANGBOARD INC

F:

**HIGHWAY 84 EAST**