



ASCENDUM

OIL ANALYSIS REPORT

| | |
|-----------------|--------|
| WEAR | NORMAL |
| CONTAMINATION | NORMAL |
| FLUID CONDITION | NORMAL |



Machine Id
VOLVO L350H 1302 (S/N 1218)
Component
Front Right Final Drive
Fluid
VOLVO SUPER WET BRAKE TRANSAXLE OIL WB102 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

| Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|----------------|-----|-------------|-----------|-------------|----------|----------|
| Sample Number | | Client Info | | ASC0004820 | --- | --- |
| Sample Date | | Client Info | | 16 May 2024 | --- | --- |
| Machine Age | hrs | Client Info | | 541 | --- | --- |
| Oil Age | hrs | Client Info | | 541 | --- | --- |
| Filter Age | hrs | Client Info | | 541 | --- | --- |
| Oil Changed | | Client Info | | Not Changed | --- | --- |
| Filter Changed | | Client Info | | Not Changed | --- | --- |
| Sample Status | | | | NORMAL | --- | --- |

WEAR

All component wear rates are normal.

| | | | | | | |
|--------------|--------|-------------|-------|------|-----|-----|
| Iron | ppm | ASTM D5185m | >1000 | 72 | --- | --- |
| Chromium | ppm | ASTM D5185m | >10 | <1 | --- | --- |
| Nickel | ppm | ASTM D5185m | >10 | 0 | --- | --- |
| Titanium | ppm | ASTM D5185m | | 0 | --- | --- |
| Silver | ppm | ASTM D5185m | | 0 | --- | --- |
| Aluminum | ppm | ASTM D5185m | >10 | 1 | --- | --- |
| Lead | ppm | ASTM D5185m | >25 | <1 | --- | --- |
| Copper | ppm | ASTM D5185m | >30 | 2 | --- | --- |
| Tin | ppm | ASTM D5185m | >10 | <1 | --- | --- |
| Vanadium | ppm | ASTM D5185m | | <1 | --- | --- |
| White Metal | scalar | *Visual | NONE | NONE | --- | --- |
| Yellow Metal | scalar | *Visual | NONE | NONE | --- | --- |

CONTAMINATION





There is no indication of any contamination in the oil.

| | | | | | | |
|------------------|--------|-------------|-------|-------|-----|-----|
| Silicon | ppm | ASTM D5185m | >30 | 12 | --- | --- |
| Potassium | ppm | ASTM D5185m | >20 | 2 | --- | --- |
| Water | | WC Method | >0.2 | NEG | --- | --- |
| Silt | scalar | *Visual | NONE | NONE | --- | --- |
| Debris | scalar | *Visual | NONE | NONE | --- | --- |
| Sand/Dirt | scalar | *Visual | NONE | NONE | --- | --- |
| Appearance | scalar | *Visual | NORML | NORML | --- | --- |
| Odor | scalar | *Visual | NORML | NORML | --- | --- |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | --- | --- |

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

| | | | | | | |
|-------------|-----|-------------|----|-------|-----|-----|
| Sodium | ppm | ASTM D5185m | | 1 | --- | --- |
| Boron | ppm | ASTM D5185m | | 115 | --- | --- |
| Barium | ppm | ASTM D5185m | | 3 | --- | --- |
| Molybdenum | ppm | ASTM D5185m | | 2 | --- | --- |
| Manganese | ppm | ASTM D5185m | | 2 | --- | --- |
| Magnesium | ppm | ASTM D5185m | | 9 | --- | --- |
| Calcium | ppm | ASTM D5185m | | 3644 | --- | --- |
| Phosphorus | ppm | ASTM D5185m | | 1283 | --- | --- |
| Zinc | ppm | ASTM D5185m | | 1587 | --- | --- |
| Sulfur | ppm | ASTM D5185m | | 11612 | --- | --- |
| Visc @ 40°C | cSt | ASTM D445 | 55 | 54.0 | --- | --- |



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : ASC0004820
Lab Number : 06195748
Unique Number : 11057871
Test Package : CONST

Received : 30 May 2024
Tested : 31 May 2024
Diagnosed : 31 May 2024 - Wes Davis

LANGBOARD INC
 HIGHWAY 84 EAST
 QUITMAN, GA
 US 31643

Contact: SERVICE MANAGER

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (229)263-8943

F: