



VOLVO A30G 740273

Bogie/Center Axle

VOLVO PREMIUM GEAR OIL 85W-140 GL-5 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP437085	VCP417082	VCP364494
	Sample Date		Client Info		25 Apr 2024	22 Aug 2023	01 Sep 2022
	Machine Age	hrs	Client Info		11987	11091	10152
	Oil Age	hrs	Client Info		3000	4000	2000
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		Not Changd	Changed	Changed
	Filter Changed		Client Info		Not Changd	Changed	Changed
	Sample Status				ATTENTION	ATTENTION	ABNORMAL
WEAR	Iron	ppm	ASTM D5185m	>900	295	437	218
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	3	5	3
	Nickel	ppm	ASTM D5185m	>10	3	4	0
	Titanium	ppm	ASTM D5185m		0	<1	0
	Silver	ppm	ASTM D5185m		0	0	0
	Aluminum	ppm	ASTM D5185m	>30	2	5	2
	Lead	ppm	ASTM D5185m	>50	0	0	0
	Copper	ppm	ASTM D5185m	>150	22	20	17
	Tin	ppm	ASTM D5185m	>20	1	1	<1
	Vanadium	ppm	ASTM D5185m		<1	0	0
	White Metal	scalar	*Visual	NONE	MODER	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	13	23	10
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2	0	2
	Water		WC Method	>0.2	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	MODER	NONE	MODER
	Debris	scalar	*Visual	NONE	NONE	NONE	A MODER
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3	1	0
The oil viscosity is lower than normal. Confirm oil type.	Boron	ppm	ASTM D5185m	111	76	57	120
	Barium	ppm	ASTM D5185m	0.0	0	0	2
	Molybdenum	ppm	ASTM D5185m	0.9	2	2	1
	Manganese	ppm	ASTM D5185m	0.0	6	7	5
	Magnesium	ppm	ASTM D5185m	39	<1	0	<1
	Calcium	ppm	ASTM D5185m	93	147	32	35
	Phosphorus	ppm	ASTM D5185m	920	1788	1706	1888
	Zinc	ppm	ASTM D5185m		63	15	22
	Sulfur	ppm	ASTM D5185m	20179	28488	24618	31252

Visc @ 40°C

cSt

ASTM D445


333


Contact/Location: KENNY HANEY - VOLVO0093

59.7

58.2

60.0





ALTA EQUIPMENT/FLAGLER CONSTRUCTION EQUIPMENT LLC Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Received 8418 PALM RIVER ROAD : VCP437085 : 30 May 2024 Lab Number : 06195770 TAMPA, FL Tested : 31 May 2024 Unique Number : 11057893 : 01 Jun 2024 - Don Baldridge US 33619 Diagnosed Test Package : MOB 1 Contact: KENNY HANEY Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. khaney@flaglerce.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (813)630-0077 F: (813)630-2233 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: KENNY HANEY - VOLVO0093 Page 2 of 2